



## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification 5 :</b>  <b>D01F 6/62, D01D 5/098</b>	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 94/08078</b>  <b>(43) International Publication Date:</b> 14 April 1994 (14.04.94)																																	
<b>(21) International Application Number:</b> PCT/US93/09308 <b>(22) International Filing Date:</b> 30 September 1993 (30.09.93)  <b>(30) Priority data:</b> 07/955,690      2 October 1992 (02.10.92)      US 08/071,590      2 June 1993 (02.06.93)      US  <b>(71) Applicant:</b> CARGILL, INCORPORATED [US/US]; 15407 McGinty Road, Wayzata, MN 55391-2399 (US).  <b>(72) Inventors:</b> GRUBER, Patrick, Richard ; 977 W. Nebraska Avenue, St. Paul, MN 55117 (US). KOLSTAD, Jeffrey, John ; 16122 Ringer Road, Wayzata, MN 55391 (US). RYAN, Christopher, M. ; 16251 125th Avenue North, Dayton, MN 55327 (US).		<b>(74) Agent:</b> BRUESS, Steven, C.; Merchant, Gould, Smith, Edell, Welter & Schmidt, 3100 Norwest Center, 90 South Seventh Street, Minneapolis, MN 55402 (US).  <b>(81) Designated States:</b> AT, AU, BB, BG, BR, BY, CA, CH, CZ, DE, DK, ES, FI, GB, HU, JP, KP, KR, KZ, LK, LU, LV, MG, MN, MW, NL, NO, NZ, PL, PT, RO, RU, SD, SE, SK, UA, UZ, VN, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).  <b>Published</b> <i>With international search report.</i> <i>Before the expiration of the time limit for amending the</i> <i>claims and to be republished in the event of the receipt of</i> <i>amendments.</i>																																	
<b>(54) Title:</b> A MELT-STABLE LACTIDE POLYMER FABRIC AND PROCESS FOR MANUFACTURE THEREOF  <div data-bbox="493 1102 1143 1751" data-label="Figure"> <table border="1"> <caption>Data points from the graph</caption> <thead> <tr> <th>Temperature (C°)</th> <th>Lactide Concentration (Wt%)</th> <th>Type</th> </tr> </thead> <tbody> <tr><td>80</td><td>0.5</td><td>LITERATURE</td></tr> <tr><td>90</td><td>0.8</td><td>LITERATURE</td></tr> <tr><td>100</td><td>1.0</td><td>LITERATURE</td></tr> <tr><td>110</td><td>1.2</td><td>LITERATURE</td></tr> <tr><td>120</td><td>1.5</td><td>LITERATURE</td></tr> <tr><td>130</td><td>1.8</td><td>LITERATURE</td></tr> <tr><td>140</td><td>2.2</td><td>LITERATURE</td></tr> <tr><td>170</td><td>3.5</td><td>EXPERIMENTAL</td></tr> <tr><td>175</td><td>3.8</td><td>EXPERIMENTAL</td></tr> <tr><td>180</td><td>4.0</td><td>EXPERIMENTAL</td></tr> </tbody> </table> </div>			Temperature (C°)	Lactide Concentration (Wt%)	Type	80	0.5	LITERATURE	90	0.8	LITERATURE	100	1.0	LITERATURE	110	1.2	LITERATURE	120	1.5	LITERATURE	130	1.8	LITERATURE	140	2.2	LITERATURE	170	3.5	EXPERIMENTAL	175	3.8	EXPERIMENTAL	180	4.0	EXPERIMENTAL
Temperature (C°)	Lactide Concentration (Wt%)	Type																																	
80	0.5	LITERATURE																																	
90	0.8	LITERATURE																																	
100	1.0	LITERATURE																																	
110	1.2	LITERATURE																																	
120	1.5	LITERATURE																																	
130	1.8	LITERATURE																																	
140	2.2	LITERATURE																																	
170	3.5	EXPERIMENTAL																																	
175	3.8	EXPERIMENTAL																																	
180	4.0	EXPERIMENTAL																																	
<b>(57) Abstract</b>  A nonwoven fabric comprised of a lactide polymer. The lactide polymer comprises a plurality of poly(lactide) polymer chains, residual lactide in concentration of less than about 2% and water in concentration of less than about 2000 parts-per-million. A process for manufacturing a nonwoven fabric with the lactide polymer composition is also disclosed.																																			

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	FR	France	MR	Mauritania
AU	Australia	GA	Gabon	MW	Malawi
BB	Barbados	GB	United Kingdom	NE	Niger
BE	Belgium	GN	Guinea	NL	Netherlands
BF	Burkina Faso	GR	Greece	NO	Norway
BG	Bulgaria	HU	Hungary	NZ	New Zealand
BJ	Benin	IE	Ireland	PL	Poland
BR	Brazil	IT	Italy	PT	Portugal
BY	Belarus	JP	Japan	RO	Romania
CA	Canada	KP	Democratic People's Republic of Korea	RU	Russian Federation
CF	Central African Republic	KR	Republic of Korea	SD	Sudan
CG	Congo	KZ	Kazakhstan	SE	Sweden
CH	Switzerland	LI	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovak Republic
CM	Cameroon	LU	Luxembourg	SN	Senegal
CN	China	LV	Latvia	TD	Chad
CS	Czechoslovakia	MC	Monaco	TG	Togo
CZ	Czech Republic	MG	Madagascar	UA	Ukraine
DE	Germany	ML	Mali	US	United States of America
DK	Denmark	MN	Mongolia	UZ	Uzbekistan
ES	Spain			VN	Viet Nam
FI	Finland				

**A MELT-STABLE LACTIDE POLYMER FABRIC  
AND PROCESS FOR MANUFACTURE THEREOF**

**BACKGROUND OF THE INVENTION**

**1. Field of the Invention**

5       The present invention relates to fabrics comprising a melt-stable, biodegradable lactide polymer composition and a process for manufacturing such fabrics from a melt-stable, biodegradable lactide polymer.

**2. Description of the Prior Art**

10       The need for and uses of fabrics, particularly nonwoven fabrics, have increased tremendously in recent years. Production of nonwoven roll goods was estimated at 2.5 billion pounds in 1992. Nonwoven fabrics are presently used for coverstock, interlinings, wipes,  
15       carrier sheets, furniture and bedding construction, filtration, apparel, insulation, oil cleanup products, cable insulating products, hospital drapes and gowns, battery separators, outerwear construction, diapers and feminine hygiene products.

20       There are basically three different manufacturing industries which make fabrics, such as nonwovens; the textile, paper and extrusion industries. The textile industry garnets, cards or aerodynamically forms textile fibers into oriented webs. The paper industry employs  
25       technology for converting dry laid pulp and wet laid paper systems into nonwoven fabrics. The extrusion industry uses at least three methods of nonwoven manufacture, those being the spunbond, melt blown and porous film methods. The melt blown method involves  
30       extruding a thermoplastic resin through a needle thin die, exposing the extruded fiber to a jet of hot air and depositing the "blown" fiber on a conveyor belt. These fibers are randomly orientated to form a web. The spunbond method also utilizes a needle thin die, but  
35       orients or separates the fibers in some manner. The porous film method employs both slit and annular dies. In one method, a sheet is extruded and drawn, fibrillization occurs and a net-like fabric results.

A problem associated with current fabric materials is that recycling of the articles containing the fabrics, such as nonwovens, is generally not cost effective. In addition, disposal generally involves creating non-degradable waste. A vivid example is the disposal of diapers. Disposable diapers rely heavily on the use of nonwovens in their construction. Millions of diapers are disposed of each year. These disposable diapers end up in landfills or compost sites. The public is becoming increasingly alarmed over diapers that are not constructed of biodegradable material. In order to address the public's concern over the environment, diaper manufacturers are turning to biodegradable materials for use in their diapers. Currently, biodegradable materials made from starch based polymers, polycaprolactones, polyvinyl alcohols, and polyhydroxybutyrate-valerate-copolymers are under consideration for a variety of different uses in the disposable article market. However, to date, there has not been a satisfactory fabric made from a biodegradable material which has properties that can withstand the present requirements of nonwoven fabrics.

Although not believed to be known as a precursor for fabrics such as nonwovens, the use of lactic acid and lactide to manufacture a biodegradable polymer is known in the medical industry. As disclosed by Nieuwenhuis et al. (U.S. Patent No. 5,053,485), such polymers have been used for making biodegradable sutures, clamps, bone plates and biologically active controlled release devices. Processes developed for the manufacture of polymers to be utilized in the medical industry have incorporated techniques which respond to the need for high purity and biocompatibility in the final product. These processes were designed to produce small volumes of high dollar-value products, with less emphasis on manufacturing cost and yield.

In order to meet projected needs for biodegradable packaging materials, others have endeavored to optimize lactide polymer processing systems. Gruber et al. (U.S. Pat. No. 5,142,023) disclose a continuous process for the manufacture of lactide polymers with controlled optical purity from lactic acid having physical properties suitable for replacing present petrochemical-based polymers.

Generally, manufacturers of polymers utilizing processes such as those disclosed by Gruber et al. will convert raw material monomers into polymer beads, resins or other pelletized or powdered products. The polymer in this form may then be then sold to end users who convert, i.e., extrude, blow-mold, cast films, blow films, thermoform, injection-mold or fiber-spin the polymer at elevated temperatures to form useful articles. The above processes are collectively referred to as melt-processing. Polymers produced by processes such as those disclosed by Gruber et al., which are to be sold commercially as beads, resins, powders or other non-finished solid forms are generally referred to collectively as polymer resins.

Prior to the present invention, it is believed that there has been no disclosure of a combination of composition control and melt stability requirements which will lead to the production of commercially viable lactide polymer nonwoven fabrics.


It is generally known that lactide polymers or poly(lactide) are unstable. The concept of instability has both negative and positive aspects. A positive aspect is the biodegradation or other forms of degradation which occur when lactide polymers or articles manufactured from lactide polymers are discarded or composted after completing their useful life. A negative aspect of such instability is the degradation of lactide polymers during processing at elevated temperatures as, for example, during melt-

processing by end-user purchasers of polymer resins. Thus, the same properties that make lactide polymers desirable as replacements for non-degradable petrochemical polymers also create undesirable effects during processing which must be overcome.

Lactide polymer degradation at elevated temperature has been the subject of several studies, including: I. C. McNeill and H. A. Leiper, Polymer Degradation and Stability, vol. 11, pp. 267-285 (1985); I. C. McNeill and H. A. Leiper, Polymer Degradation and Stability, vol. 11, pp. 309-326 (1985); M. C. Gupta and V. G. Deshmukh, Colloid & Polymer Science, vol. 260, pp. 308-311 (1982); M. C. Gupta and V. G. Deshmukh, Colloid & Polymer Science, vol. 260, pp. 514-517 (1982); Ingo Luderwald, Dev. Polymer Degradation, vol. 2, pp. 77-98 (1979); Domenico Garozzo, Mario Giuffrida, and Giorgio Montaudo, Macromolecules, vol. 19, pp. 1643-1649 (1986); and, K. Jamshidi, S. H. Hyon and Y. Ikada, Polymer, vol. 29, pp. 2229-2234 (1988).

It is known that lactide polymers exhibit an equilibrium relationship with lactide as represented by the reaction below:


5



10

15

20



25

No consensus has been reached as to what the primary degradation pathways are at elevated processing temperatures. One of the proposed reaction pathways includes the reaction of a hydroxyl end group in a "back-biting" reaction to form lactide. This equilibrium reaction is illustrated above. Other proposed reaction pathways include: reaction of the hydroxyl end group in a "back-biting" reaction to form cyclic oligomers, chain scission through hydrolysis of the ester bonds, an intramolecular beta-elimination reaction producing a new acid end group and an unsaturated carbon-carbon bond, and radical chain decomposition reactions. Regardless of the mechanism or mechanisms involved, the fact that substantial degradation occurs at elevated temperatures, such as those used by melt-processors, creates an obstacle to use of lactide polymers as a replacement for petrochemical-based polymers. It is apparent that degradation of the polymer during melt-processing must be reduced to a commercially acceptable rate while the

polymer maintains the qualities of biodegradation or compostability which make it so desirable. It is believed this problem has not been addressed prior to the developments disclosed herein.

5 As indicated above, poly(lactide)s have been produced in the past, but primarily for use in medical devices. These polymers exhibit biodegradability, but also a more stringent requirement of being bioresorbable or biocompatible. As disclosed by M. Vert, Die  
10 Ingwandte Makromolekulare Chemie, vol. 166-167, pp. 155-168 (1989), "The use of additives is precluded because they can leach out easily in body fluids and then be recognized as toxic, or, at least, they can be the source of fast aging with loss of the properties which  
15 motivated their use. Therefore, it is much more suitable to achieve property adjustment through chemical or physical structure factors, even if aging is still a problem." Thus, work aimed at the bioresorbable or biocompatible market focused on poly(lactide) and blends  
20 which did not include any additives.

Other disclosures in the medical area include Nieuwenhuis (European Patent No. 0 314 245), Nieuwenhuis (U.S. Patent No. 5,053,485), Eitenmuller (U.S. Patent No. 5,108,399), Shinoda (U.S. Patent No. 5,041,529),  
25 Fouty (Canadian Patent No. 808,731), Fouty (Canadian Patent No. 923,245), Schneider (Canadian Patent No. 863,673), and Nakamura et al., Bio. Materials and Clinical Applications, Vol. 7, p. 759 (1987). As  
disclosed in these references, in the high value, low  
30 volume medical specialty market, poly(lactide) or lactide polymers and copolymers can be given the required physical properties by generating lactide of very high purity by means of such methods as solvent extraction or recrystallization followed by  
35 polymerization. The polymer generated from this high purity lactide is a very high molecular weight product which will retain its physical properties even if



substantial degradation occurs and the molecular weight drops significantly during processing. Also, the polymer may be precipitated from a solvent in order to remove residual monomer and catalysts. Each of these treatments add stability to the polymer, but clearly at a high cost which would not be feasible for lactide polymer compositions which are to be used to replace inexpensive petrochemical-based polymers in the manufacture of nonwoven products.

Furthermore, it is well-known that an increase in molecular weight generally results in an increase in a polymer's viscosity. A viscosity which is too high can prevent melt-processing of the polymer due to physical/mechanical limitations of the melt-processing equipment. Melt-processing of higher molecular weight polymers generally requires the use of increased temperatures to sufficiently reduce viscosity so that processing can proceed. However, there is an upper limit to temperatures used during processing. Increased temperatures increase degradation of the lactide polymer, as the previously-cited studies disclose.

Jamshidi et al., Polymer, Vol. 29, pp. 2229-2234 (1988) disclose that the glass transition temperature of a lactide polymer,  $T_g$ , plateaus at about 57°C for poly(lactide) having a number average molecular weight of greater than 10,000. It is also disclosed that the melting point,  $T_m$ , of poly (L-lactide) levels off at about 184°C for semi-crystalline lactide polymers having a number average molecular weight of about 70,000 or higher. This indicates that at a relatively low molecular weight, at least some physical properties of lactide polymers plateau and remain constant.

Sinclair et al. (U.S. Patent No. 5,180,765) disclose the use of residual monomer, lactic acid or lactic acid oligomers to plasticize poly(lactide) polymers, with plasticizer levels of 2-60%. Loomis (U.S. Patent No.

5,076,983) discloses a process for manufacturing a self-supporting film in which the oligomers of hydroxy acids are used as plasticizing agents. Loomis and Sinclair et al. disclose that the use of a plasticizer such as  
5 lactide or lactic acid is beneficial to produce more flexible materials which are considered to be preferable. Sinclair et al., however, disclose that residual monomer can deposit out on rollers during processing. Loomis also recognizes that excessive  
10 levels of plasticizer can cause unevenness in films and may separate and stick to and foul processing equipment. Thus, plasticizing as recommended, negatively impacts melt-processability in certain applications.

Accordingly, a need exists for a lactide polymer  
15 composition which is melt-stable under the elevated temperatures common to melt-processing resins in the manufacture of fabrics, such as nonwovens. The needed melt-stable polymer composition must also exhibit sufficient compostability or degradability after its  
20 useful life as a fabric. Further, the melt-stable polymer must be processable in existing melt-processing equipment, by exhibiting sufficiently low viscosities at melt-processing temperatures while polymer degradation and lactide formation remains below a point of  
25 substantial degradation and does not cause excessive fouling of processing equipment. Furthermore, the polymer lactide must retain its molecular weight, viscosity and other physical properties within commercially-acceptable levels through the fabric  
30 manufacturing process. It will be further appreciated that a need also exists for a process for manufacturing fabrics such as nonwoven fabrics. The present invention addresses these needs as well as other problems associated with existing lactide polymer compositions  
35 and manufacturing processes. The present invention also offers further advantages over the prior art, and solves other problems associated therewith.

SUMMARY OF THE INVENTION

According to the present invention, a fabric, such as a nonwoven fabric, comprising poly(lactide) fibers is provided. A first portion of the fibers comprises a  
5 melt-stable lactide polymer composition comprising: poly(lactide) chains having a number average molecular weight of at least 10,000, and preferably from about 10,000 to about 300,000; lactide in a concentration of less than about 2% by weight; and optionally water in a  
10 concentration of less than about 2,000 parts per million. A process for the manufacture of the fabric is also provided. For the purposes of the present invention, the fabric may be manufactured from any number of methods and is not to be limited by the  
15 particular method.

Optionally, stabilizing agents in the form of anti-oxidants and water scavengers may be added. Further, plasticizers, nucleating agents and/or anti-blocking agents may be added. The resultant fabric is  
20 biodegradable and may be disposed of in an environmentally sound fashion.

Poly(lactide) is a polymeric material which offers unique advantages as a fiber for nonwovens not only in the biodegradable sense, but in the manufacturing  
25 process as well.

Poly(lactide) offers advantages in the formation of the nonwoven fabric in a melt extrusion process. One problem that is sometimes encountered in the extrusion of fibers into a nonwoven web is poor adhesion of the  
30 fibers to one another upon cooling. Two characteristics of poly(lactides) lend themselves to enhanced adhesion: low viscosity and high polarity. Mechanical adhesion, the interlocking of fibers at adjoining points, increases as the viscosity decreases. An advantage of  
35 poly(lactide) is that the viscosity lends itself well to fiber formation. Thus, poly(lactide) fibers adhere to one another well, resulting in a web with added

strength. Also, because the surface is typically polar for most fibers, the high polarity of the poly(lactide) offers many dipole-dipole interactions, further resulting in enhanced adhesion.

5 In melt blown processes, the fibers of the present invention have small diameters which are beneficial for many applications. The present fibers can have diameters of less than about 5  $\mu\text{m}$ .

The fibers of a nonwoven web of the present  
10 invention are superior to typical polypropylene nonwoven webs in diaper construction. The typical construction of a diaper comprises an outer, water impervious back sheet, a middle, absorbent layer and an inner layer, which is in contact with the diaper wearer. The inner  
15 layer is typically made from a soft, nonwoven material such as a polypropylene nonwoven web. However, polypropylene, due to its low polarity, has to be surface modified such that the urine passes through the inner layer, rather than being repelled. A significant  
20 advantage of the present invention is that the polarity of the poly(lactide) (without surface treatment) is ideally suited such that urine readily passes through the nonwoven web, but is not absorbed by the layer. Thus, the poly(lactide) web of the present invention is  
25 a superior inner layer for diaper construction. The present invention may also be employed in incontinent and feminine hygiene products.

A fabric, such as a nonwoven, of the present invention also may be used in packaging and bagging  
30 operations. Food packaging which does not require water tight packaging but requires breathability is an example of a use of the present invention. Bags such as leaf or yard bags may also be made from a nonwoven fabric of the present invention. The fabric is porous to allow air to  
35 enter the bag to begin decomposing the leaves. This is advantageous over present leaf bags, which do not allow air to penetrate into the leaf cavity. Further, the

present nonwoven fabric, when used as a leaf bag, decomposes along with the leaves, thus minimizing the adverse environmental impact of the leaf bags.

Poly(lactide) processes at lower temperatures which  
5 allows the fiber to be extruded at lower temperatures than traditional polymers. This results in a cost savings to the converter because the extrusion equipment will not require as much power when run at lower temperatures. There is also increased safety associated  
10 with lower temperatures.

A significant advantage of poly(lactide) over many fabrics used today such as polypropylene is its biodegradability. The continued depletion of landfill space and the problems associated with incineration of  
15 waste have led to the need for development of a truly biodegradable fabric to be utilized as a substitute for non-biodegradable or partially biodegradable petrochemical-based nonwoven fabrics. Furthermore, a poly(lactide) nonwoven web, unlike other biodegradable  
20 polymers, is believed not to support microbial growth. Starch or other biodegradable polymers, when exposed to warm, damp environments, will promote the growth of unhealthy microbes. This is undesirable in the diaper industry. Thus the present invention has yet another  
25 advantage over prior biodegradable polymers.

The above described features and advantages along with various other advantages and features of novelty are pointed out with particularity in the claims of the present application. However, for a better  
30 understanding of the invention, its advantages, and objects attained by its use, reference should be made to the drawings which form a further part of the present application and to the accompanying descriptive matter in which there is illustrated and described preferred  
35 embodiments of the present invention.

**BRIEF DESCRIPTION OF THE DRAWINGS**

In the drawings, in which like reference numerals indicate corresponding parts or elements of preferred embodiments of the present invention throughout the  
5 several views;

Fig. 1 is a schematic representation of a preferred process for the manufacture of a melt-stable lactide polymer composition; and

Fig. 2 is a graph showing the equilibrium  
10 relationship between lactide and poly(lactide) at various temperatures.

Fig. 3 is a graph showing the relationship between meso-lactide concentration and energy of melting.

**15 DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENT(S)**

The lactide polymer compositions used in fabrics disclosed herein focus on meeting the requirements of the end user melt-processor of a lactide polymer resin such as that produced from a process disclosed by Gruber  
20 et al. However, the present invention is directed to a poly(lactide) fiber and is not limited to the lactide polymer composition or process of Gruber et al. Any lactide polymer composition, which comes within the scope of this invention, may be used as a fiber for a  
25 fabric, particularly a nonwoven fabric. As disclosed herein, the problems of degradation, fouling, and lactide formation during melt-processing of lactide polymers are addressed through suggested ranges of molecular weights and compositional limits on impurities  
30 such as residual monomer, water and catalyst along with the use of stabilizing agents and catalyst-deactivating agents.

In general, according to the present invention, a melt-stable lactide polymer fabric and a process for  
35 manufacturing a melt-stable lactide polymer fabric from a melt-stable lactide polymer are disclosed. Lactide polymers are useful due to their biodegradable nature.

Furthermore, lactide polymers are compostable as illustrated in Example 15 below. Applicants believe the hydrolysis of the ester may be the key to or the first step in degradation of a lactide polymer composition.

- 5 The mechanism of degradation is not key to the fabric of the present invention, however it must be recognized that such degradation makes lactide polymers desirable as replacements for presently-utilized non-degradable petrochemical-based polymers used for fabrics, such as  
10 nonwovens.

Applicants have found that the instability of lactide polymers which leads to the beneficial degradation discussed above also creates processing problems. These processing problems include generation  
15 of lactide monomer at elevated temperatures and loss in molecular weight believed due to chain scission degradation of the ester bonds and other depolymerization reactions which are not completely understood. No consensus has been reached as to what  
20 are the primary degradation pathways at elevated processing temperatures. As previously disclosed, these may include such pathways as equilibrium-driven depolymerization of lactide polymers to form lactide and chain scission through hydrolysis of the ester bonds  
25 along with other pathways. For purposes of the present invention, the exact mechanism of degradation at elevated temperatures is not critical.

- It is to be understood, however, that degradation of lactide polymers is both beneficial and detrimental.  
30 Benefits derive from degradability when articles manufactured from such polymers are discarded. The same or similar types of degradation are detrimental if they occur during processing or prior to the end of the article's useful life.

### Melt-Processing

It is believed that a manufacturer of lactide polymers from a lactide monomer will produce a lactide polymer resin which is in the form of beads or pellets.

5 The melt-processor will convert the resin to a fiber for a fabric by elevating the temperature of the resin above at least its glass transition temperature but normally higher and extruding the fiber into a fabric, such as a nonwoven. It is to be understood that the conditions of

10 elevated temperatures used in melt-processing cause degradation of lactide polymers during processing. Degradation under melt-processing conditions is shown experimentally in Example 7 based on equilibrium, Example 10 based on catalyst concentration, Example 11

15 based on catalyst activity, Example 13 based on use of stabilizers and Example 14 based on moisture content. As can be seen in these examples, it is understood that several factors appear to affect the rate of degradation during melt-processing. Applicants have addressed these

20 factors in a combination of compositional requirements and the addition of stabilizing or catalyst-deactivating agents to result in a polymer of lactide which is melt-stable.

In addition, melt-processing frequently produces

25 some proportion of trimmed or rejected material. Environmental concerns and economical efficiencies dictate that this material be reused, typically by regrinding and adding back the material into the polymer feed. This introduces additional thermal stress on the

30 polymer and increases the need for a melt-stable polymer composition.

### Melt Stability

The lactide polymers of the present invention are melt-stable. By "melt-stable" it is meant generally

35 that the lactide polymer, when subjected to melt-processing techniques, adequately maintains its physical properties and does not generate by-products in



sufficient quantity to foul or coat processing equipment. The melt-stable lactide polymer exhibits reduced degradation and/or reduced lactide formation relative to known lactide polymers. It is to be understood that degradation will occur during melt-processing. The compositional requirements and use of stabilizing agents as disclosed herein reduces the degree of such degradation to a point where physical properties are not significantly affected by melt-processing and fouling by impurities or degradation by-products such as lactide does not occur. Furthermore, the melt-stable polymer should be melt-processable in melt-processing equipment such as that available commercially. Further, the polymer will preferably retain adequate molecular weight and viscosity. The polymer should preferably have sufficiently low viscosity at the temperature of melt-processing so that the extrusion equipment may create an acceptable nonwoven fabric. The temperature at which this viscosity is sufficiently low will preferably also be below a temperature at which substantial degradation occurs.

#### Polymer Composition

The melt-stable lactide polymer fabric of the present invention comprises poly(lactide) polymer chains having a number average molecular weight of at least 10,000 and preferably from about 10,000 to about 300,000. In a preferred composition for a melt blown nonwoven, the number average molecular weight ranges from about 15,000 to about 100,000. In the most preferred composition, the number average molecular weight ranges from about 20,000 to about 80,000. In a spunbond nonwoven fabric, the preferred number average molecular weight range is from about 50,000 to about 250,000. In a most preferred embodiment, the number average molecular weight range is from about 75,000 to about 200,000.

As detailed in Example 9, it appears that the physical properties such as modulus, tensile strength, percentage elongation at break, impact strength, flexural modulus, and flexural strength remain statistically constant when the lactide polymer samples are above a threshold molecular weight. The lower limit of molecular weight of the polymer compositions of the present invention is set at a point above the threshold of which a fiber has sufficient diameter and density.

In other words, the molecular weight cannot be lower than is necessary to achieve a targeted fiber diameter and density. As detailed in Example 22, there is a practical upper limit on molecular weight based on increased viscosity with increased molecular weight. In order to melt-process a high molecular weight lactide polymer, the melt-processing temperature must be increased to reduce the viscosity of the polymer. As pointed out in the Examples, the exact upper limit on molecular weight must be determined for each melt-processing application in that required viscosities vary and residence time within the melt-processing equipment will also vary. Thus, the degree of degradation in each type of processing system will also vary. Based on the disclosure of Example 22, it is believed that one could determine the suitable molecular weight upper limit for meeting the viscosity and degradation requirements in any application.

Lactide polymers can be in either an essentially amorphous form or in a semi-crystalline form. For various applications it will be desirable to have the polymer in one of these configurations. As detailed in Example 24, the desired range of compositions for semi-crystalline poly(lactide) is less than about 12% by weight meso-lactide and the remaining percent by weight either L-lactide or D-lactide, with L-lactide being more readily available. A more preferred composition contains less than about 9% by weight meso-lactide with

the remainder being substantially all L-lactide.

For applications where an amorphous polymer is desired, the preferred composition of the reaction mixture is above 9% by weight meso-lactide and a more preferred composition contains above 12% by weight meso-lactide with the remaining lactide being substantially all L-lactide mixture, or D-lactide can be used to control the potential crystallinity in a predominantly L-lactide mixture.

10 Addition of even small amounts of meso-lactide to the polymerization mixture results in a polymer which is even slower to crystallize than polymerization mixtures having lesser amounts of meso-lactide, as detailed in Example 23. Beyond about 12% meso content the polymer  
15 remains essentially amorphous following a typical annealing procedure. This contrasts with the behavior of D,L-lactide, which can be added at a concentration of 20% to the polymerization mixture and still produce a semi-crystalline polymer following the annealing  
20 procedure. These results are detailed in Example 24.

There are three main methods to increase the rate of crystallization. One is to increase chain mobility at low temperatures, by adding, for example, a plasticizing agent. The plasticizer must be selected carefully,  
25 however, and preferably will be of limited compatibility so that it will migrate to the amorphous phase during crystallization. Dioctyl adipate is an example of a plasticizer which helps crystallization rates in poly(lactide), as detailed in Example 25. A second  
30 method to increase the rate of crystallization is to add a nucleating agent, as detailed in Example 26. A third method is to orient the polymer molecules. Orientation can be accomplished by drawing during film casting, drawing of fibers, blowing films, stretching of film or  
35 sheet after it is cast (in multiple directions, if desired), or by the flow of polymer through a small opening in a die. The alignment generated helps to

increase the rate of crystallization, as detailed in Example 27.

Heat setting may also be employed to increase the degree of crystallinity in the fibers. Heat setting  
5 involves exposing the fabric to elevated temperatures, as shown in *Plastics Extrusion Technology*, F. Hensen (ed), Hanser Publishers, New York, 1988, pp 308, 324. It is preferred to heat set with the fiber or nonwoven fabric under tension to reduce shrinkage during the  
10 setting process.

Applicants recognize that an essentially amorphous lactide polymer may have some crystallinity. Crystalline poly L-lactide exhibits an endotherm of roughly 92 Joules per gram at its melting temperature of  
15 170°-190°C. The melting point changes with composition. The degree of crystallinity is roughly proportional to the endotherm on melting. For purposes of the present invention, it is meant by an amorphous or non-crystalline poly(lactide) to be a poly(lactide) or  
20 lactide polymer which exhibits a melting endotherm of less than about 10 Joules per gram in the temperature range of about 130-200°C. Semi-crystalline poly(lactide) exhibits a melting endotherm above about 10 joules per gram.

25 The residual monomer concentration in the melt-stable lactide polymer composition is less than about 2% by weight. In a preferred composition, the lactide concentration is less than about 1% by weight, and a most preferred composition has less than about 0.5% by  
30 weight of lactide. Contrary to disclosures in the art, Applicants have found that the monomer cannot be used as a plasticizing agent in the resin of the present invention due to significant fouling of the extrusion equipment. As detailed in Example 16, it is believed  
35 the low levels of monomer concentration do not plasticize the final polymer.

The water concentration within the melt-stable lactide polymer composition is less than about 2,000 parts-per-million. Preferably this concentration is less than 500 parts-per-million and most preferably less than about 100 parts-per-million. As detailed in Example 14, the polymer melt-stability is significantly affected by moisture content. Thus, the melt-stable polymer of the present invention must have the water removed prior to melt-processing. Applicants recognize that water concentration may be reduced prior to processing the polymerized lactide to a resin. Thus, moisture control could be accomplished by packaging such resins in a manner which prevents moisture from contacting the already-dry resin. Alternatively, the moisture content may be reduced at the melt-processor's facility just prior to the melt-processing step in a dryer. Example 14 details the benefit of drying just prior to melt-processing and also details the problems encountered due to water uptake in a polymer resin if not stored in a manner in which moisture exposure is prevented or if not dried prior to melt-processing. As detailed in these examples, Applicants have found that the presence of water causes excessive loss of molecular weight which may affect the physical properties of the melt-processed polymer.

In a preferred composition of the present invention, a stabilizing agent is included in the polymer formulation to reduce degradation of the polymer during production, devolatilization, drying and melt processing by the end user. The stabilizing agents recognized as useful in the present nonwoven fibers may include antioxidants and/or water scavengers. Preferred antioxidants are phosphite-containing compounds, hindered phenolic compounds or other phenolic compounds. The antioxidants include such compounds as trialkyl phosphites, mixed alkyl/aryl phosphites, alkylated aryl phosphites, sterically hindered aryl phosphites,

aliphatic spirocyclic phosphites, sterically hindered phenyl spirocyclics, sterically hindered bisphosphonites, hydroxyphenyl propionates, hydroxy benzyls, alkylidene bisphenols, alkyl phenols, aromatic amines, thioethers, hindered amines, hydroquinones and mixtures thereof. As detailed in Example 13, many commercially-available stabilizing agents have been tested and fall within the scope of the present melt-stable lactide polymer nonwoven fabric composition.

Biodegradable antioxidants are particularly preferred.

The water scavengers which may be utilized in preferred embodiments of the melt-stable lactide polymer nonwoven fiber include: carbodiimides, anhydrides, acyl chlorides, isocyanates, alkoxy silanes, and desiccant materials such as clay, alumina, silica gel, zeolites, calcium chloride, calcium carbonate, sodium sulfate, bicarbonates or any other compound which ties up water. Preferably the water scavenger is degradable or compostable. Example 19 details the benefits of utilizing a water scavenger.

In a preferred composition of the present invention, a plasticizer is included in the polymer formulation to improve the nonwoven fiber quality of the lactide polymer. More particularly, plasticizers reduce the melt viscosity at a given temperature of poly(lactide), which aides in processing and extruding the polymer at lower temperatures and may improve flexibility and reduce cracking tendencies of the finished fabric. Plasticizers also lower the melt viscosity of poly(lactide), thereby making it easier to draw-down the fibers to a small diameter.

A plasticizer is useful in concentration levels of about 1 to 35%. Preferably, a plasticizer is added at a concentration level of about 5 to 25%. Most preferably, a plasticizer is added at a concentration level of about 8 to 25%.

Selection of a plasticizing agent requires screening of many potential compounds and consideration of several criteria. For use in a biodegradable nonwoven fabric the preferred plasticizer is to be biodegradable, non-  
5 toxic and compatible with the resin and relatively nonvolatile.

Plasticizers in the general classes of alkyl or aliphatic esters, ether, and multi-functional esters and/or ethers are preferred. These include alkyl  
10 phosphate esters, dialkylether diesters, tricarboxylic esters, epoxidized oils and esters, polyesters, polyglycol diesters, alkyl alkylether diesters, aliphatic diesters, alkylether monoesters, citrate esters, dicarboxylic esters, vegetable oils and their  
15 derivatives, and esters of glycerine. Most preferred plasticizers are tricarboxylic esters, citrate esters, esters of glycerine and dicarboxylic esters. Citroflex A4<sup>®</sup> from Morflex is particularly useful. These esters are anticipated to be biodegradable. Plasticizers  
20 containing aromatic functionality or halogens are not preferred because of their possible negative impact on the environment.

For example, appropriate non-toxic character is exhibited by triethyl citrate, acetyltriethyl citrate,  
25 tri-n-butyl citrate, acetyltri-n-butyl citrate, acetyltri-n-hexyl citrate, n-butyltri-n-hexyl citrate and dioctyl adipate. Appropriate compatibility is exhibited by acetyltri-n-butyl citrate and dioctyl adipate. Other compatible plasticizers include any  
30 plasticizers or combination of plasticizers which can be blended with poly(lactide) and are either miscible with poly(lactide) or which form a mechanically stable blend. Corn oil and mineral oil were found to be incompatible when used alone with poly(lactide) because of phase  
35 separation (not mechanically stable) and migration of the plasticizer.

Volatility is determined by the vapor pressure of the plasticizer. An appropriate plasticizer must be sufficiently non-volatile such that the plasticizer stays substantially in the resin formulation throughout the process needed to produce the nonwoven fabric. Excessive volatility can lead to fouling of process equipment, which is observed when producing fabrics by melt processing poly(lactide) with a high lactide content. Preferred plasticizers should have a vapor pressure of less than about 10 mm Hg at 170°C, more preferred plasticizers should have a vapor pressure of less than 10 mm Hg at 200°C. Lactide, which is not a preferred plasticizer, has a vapor pressure of about 40 mm Hg at 170°C. Example 6 highlights useful plasticizers for the present invention.

In a preferred composition, nucleating agents may be incorporated during polymerization. Nucleating agents may include selected plasticizers, finely divided minerals, organic compounds, salts of organic acids and imides and finely divided crystalline polymers with a melting point above the processing temperature of poly(lactide). Examples of useful nucleating agents include talc, sodium salt of saccharin, calcium silicate, sodium benzoate, calcium titanate, boron nitride, copper phthalocyanine, isotactic polypropylene, low molecular weight poly(lactide) and polybutylene terephthalate.

In a preferred composition, fillers may be useful to prevent blocking or sticking of layers or rolls of the nonwoven fabric during storage and transport. Inorganic fillers include clays and minerals, either surface modified or not. Examples include talc, diatomaceous earth, silica, mica, kaolin, titanium dioxide, and wollastonite. Preferred inorganic fillers are environmentally stable and non-toxic.



Organic fillers include a variety of forest and agricultural products, either with or without modification. Examples include cellulose, wheat, starch, modified starch, chitin, chitosan, keratin, 5 cellulosic materials derived from agricultural products, gluten, nut shell flour, wood flour, corn cob flour, and guar gum. Preferred organic fillers are derived from renewable sources and are biodegradable. Fillers may be used either alone or as mixtures of two or more fillers. 10 Example 5 highlights useful anti-blocking fillers for the present invention.

Surface treatments may also be used to reduce blocking. Such treatments include corona and flame treatments which reduce the surface contact between the 15 poly(lactide) based fabric and the adjacent surface.

For certain applications, it is desirable for the fabric to be modified to alter the water transport properties. Surfactants may be incorporated into the web of the present invention to increase the water 20 transport properties.

Surfactants which are useful can be subdivided into cationic, anionic, and nonionic agents.

With regard to cationic compounds, the active molecule part generally consists of a voluminous cation 25 which often contains a long alkyl residue (e.g. a quaternary ammonium, phosphonium or sulfonium salt) whereby the quaternary group can also occur in a ring system (e.g. imidazoline). In most cases, the anion is the chloride, methosulfate or nitrate originating from 30 the quaternization process.

In the anionic compounds, the active molecule part in this class of compounds is the anion, mostly an alkyl sulfonate, sulfate or phosphate, a dithiocarbamate or carboxylate. Alkali metals often serve as cations.

35 Nonionic antistatic agents are uncharged surface-active molecules of a significantly lower polarity than the above mentioned ionic compounds and include

polyethylene glycol esters or ethers, fatty acid esters or ethanolamides, mono-or diglycerides or ethoxylated fatty amines. The above surfactants may also act as antistatic agents, which may be desirable.

- 5       Pigments or color agents may also be added as necessary. Examples include titanium dioxide, clays, calcium carbonate, talc, mica, silica, silicates, iron oxides and hydroxides, carbon black and magnesium oxide.

- In the manufacture of the melt-stable lactide
- 10       polymer compositions of the present invention, the reaction to polymerize lactide is catalyzed. Many catalysts have been cited in literature for use in the ring-opening polymerization of lactones. These include but are not limited to:  $\text{SnCl}_2$ ,  $\text{SnBr}_2$ ,  $\text{SnCl}_4$ ,  $\text{SnBr}_4$ ,
- 15       aluminum alkoxides, tin alkoxides, zinc alkoxides,  $\text{SnO}$ ,  $\text{PbO}$ ,  $\text{Sn}$  (2-ethyl hexanoates),  $\text{Sb}$  (2-ethyl hexanoates),  $\text{Bi}$  (2-ethyl hexanoates),  $\text{Na}$  (2-ethyl hexanoates) (sometimes called octoates),  $\text{Ca}$  stearates,  $\text{Mg}$  stearates,  $\text{Zn}$  stearates, and tetraphenyltin. Applicants have also
- 20       tested several catalysts for polymerization of lactide at  $180^\circ\text{C}$  which include: tin(II) bis(2-ethyl hexanoate) (commercially available from Atochem, as Fascat 2003, and Air Products as DABCO T-9), dibutyltin diacetate (Fascat 4200<sup>®</sup>, Atochem), butyltin tris(2-ethyl hexanoate)
- 25       (Fascat 9102<sup>®</sup>, Atochem), hydrated monobutyltin oxide (Fascat 9100<sup>®</sup>, Atochem), antimony triacetate (S-21, Atochem), and antimony tris(ethylene glycoxide) (S-24, Atochem). Of these catalysts, tin(II) bis(2-ethyl hexanoate), butyltin tris(2-ethyl hexanoate) and
- 30       dibutyltin diacetate appear to be most effective.

- Applicants have found the use of catalysts to polymerize lactide significantly affects the stability of the resin product. It appears the catalyst as incorporated into the polymer also is effective at
- 35       catalyzing the reverse depolymerization reaction. Example 10 details the effect of residual catalyst on degradation. To minimize this negative effect, in a

preferred composition, the residual catalyst level in the resin is present in a molar ratio of initial monomer-to-catalyst greater than about 3,000:1, preferably greater than about 5,000:1 and most preferably greater than about 10,000:1. Applicants believe a ratio of about 20,000:1 may be used, but polymerization will be slow. Optimization of catalyst levels and the benefits associated therewith are detailed in Example 20. Applicants have found that when the catalyst level is controlled within these parameters, catalytic activity is sufficient to polymerize the lactide while sufficiently low to enable melt-processing without adverse effect when coupled with low residual monomer level and low water concentration as described above in polymers of molecular weight between 10,000 to about 300,000. It is believed in most applications the addition of a stabilizing agent may be unnecessary if catalyst level is optimized.

Applicants have also found that catalyst concentration may be reduced subsequent to polymerization by precipitation from a solvent. Example 21 demonstrates potential catalyst removal by precipitation from a solvent. This produces a resin with reduced catalyst concentration. In an alternative embodiment, the catalyst means for catalyzing the polymerization of lactide to form the poly(lactide) polymer chains which was incorporated into the melt-stable lactide polymer composition during polymerization is deactivated by including in the melt-stable lactide polymer composition a catalyst deactivating agent in amounts sufficient to reduce catalytic depolymerization of the poly(lactide) polymer chains. Example 11 details the benefits of utilizing a catalyst deactivating agent. Such catalyst-deactivating agents include hindered, alkyl, aryl and phenolic hydrazides, amides of aliphatic and aromatic mono- and dicarboxylic acids, cyclic amides, hydrazones and bishydrazones of aliphatic and

- aromatic aldehydes, hydrazides of aliphatic and aromatic mono- and dicarboxylic acids, bis-acylated hydrazine derivatives, and heterocyclic compounds. A preferred metal deactivator is Irganox® MD1024 from Ciba-Geigy.
- 5 Biodegradable metal deactivators are particularly preferred.

In an alternative embodiment, the catalyst concentration is reduced to near zero by utilizing a solid-supported catalyst to polymerize lactide. The

10 feasibility of utilizing such a catalyst is detailed in Example 8. It is believed catalysts which may be utilized include supported metal catalysts, solid acid catalysts, acid clays, alumina silicates, alumina, silica and mixtures thereof.

- 15 In a preferred composition, the catalyst usage and/or deactivation is controlled to reduce depolymerization of the poly(lactide) polymer during melt-processing to less than about 2% by weight generation of lactide from a devolatilized sample in the
- 20 first hour at 180°C and atmospheric pressure. More preferably, the amount of lactide generated is less than about 1% by weight in the first hour and most preferably less than about 0.5% by weight in the first hour.

- A preferred melt-stable lactide polymer composition
- 25 is the reaction product of polymerization of lactide at a temperature greater than about 160°C. Applicants have found that polymerization at higher temperatures result in a characteristically different polymer which is believed to have improved melt stability due to
- 30 increased transesterification during polymerization. The benefits of higher temperature polymerization are detailed in Example 12.

#### Melt-Stable Lactide Polymer Process

- The process for the manufacture of a melt-stable
- 35 lactide polymer comprises the steps of first providing a lactide mixture wherein the mixture contains about 0.5% by weight to about 50% by weight meso-lactide and about

99.5% by weight or less L-lactide and/or D-lactide. Such purified lactide stream may be such as that produced in the process disclosed by Gruber et al., although the source of lactide is not critical to the present invention.

The lactide mixture is polymerized to form a lactide polymer or poly(lactide) with some residual unreacted monomer in the presence of a catalyst means for catalyzing the polymerization of lactide to form poly(lactide). Catalysts suitable for such polymerization have been listed previously. The concentration of catalysts utilized may be optimized as detailed in the following examples and discussed previously.

In a preferred embodiment, a stabilizing agent, which may be an antioxidant and/or a water scavenger is added to the lactide polymer. It is recognized that such stabilizing agents may be added simultaneously with or prior to the polymerization of the lactide to form the lactide polymer. The stabilizing agent may also be added subsequent to polymerization.

As previously disclosed, the catalyst usage is adjusted and/or deactivation agent is added in a sufficient amount to reduce depolymerization of poly(lactide) during melt-processing to less than 2% by weight generation of lactide from a devolatilized sample in the first hour at 180°C and atmospheric pressure. More preferably, the stabilizing agent controls lactide generation to less than 1% by weight and most preferably less than 0.5% by weight in the first hour at 180°C and atmospheric pressure. Alternatively, the control of catalyst concentration to optimize the balance between necessary catalytic activity to produce poly(lactide) versus the detrimental effects of catalytic depolymerization or degradation of the lactide polymer may be utilized to obviate the need for adding a stabilizing agent.

The lactide polymer is then devolatilized to remove unreacted monomer which may also be a by-product of decomposition reactions or the equilibrium-driven depolymerization of poly(lactide). Any residual water  
5 which may be present in the polymer would also be removed during devolatilization, although it is recognized that a separate drying step may be utilized to reduce the water concentration to less than about 2,000 parts-per-million. The devolatilization of the  
10 lactide polymer may take place in any known devolatilization process. The key to selection of a process is operation at an elevated temperature and usually under conditions of vacuum to allow separation of the volatile components from the polymer. Such  
15 processes include a stirred tank devolatilization or a melt-extrusion process which includes a devolatilization chamber and the like. An inert gas sweep is useful for improved devolatilization.

In a preferred process for manufacture of a melt-  
20 stable lactide polymer composition, the process also includes the step of adding a molecular weight control agent to the lactide prior to catalyzing the polymerization of the lactide. For example, molecular weight control agents include active hydrogen-bearing  
25 compounds, such as lactic acid, esters of lactic acid, alcohols, amines, glycols, diols and triols which function as chain-initiating agents. Such molecular weight control agents are added in sufficient quantity to control the number average molecular weight of the  
30 poly(lactide) to between about 10,000 and about 300,000.

Next referring to Figure 1 which illustrates a preferred process for producing a melt-stable lactide polymer composition. A mixture of lactides enters a mixing vessel (3) through a pipeline (1). A catalyst  
35 for polymerizing lactide is also added through a pipeline (13). Within mixing vessel (3) a stabilizing agent may be added through a pipeline (2). A water

scavenger may also be added through the pipeline (2). The stabilized lactide mixture is fed through a pipeline (4) to a polymerization process (5). The polymerized lactide or lactide polymer leaves the polymerization process through a pipeline (6). The stream is fed to a second mixing vessel (8) within which a stabilizing agent and/or catalyst deactivating agent may be added through a pipeline (7). The stabilized lactide polymer composition is then fed to a devolatilization process (10) through a pipeline (9). Volatile components leave the devolatilization process through a pipeline (11) and the devolatilized lactide polymer composition leaves the devolatilization process (10) in a pipeline (12). The devolatilized lactide composition is fed to a resin-finishing process (14). Within the resin-finishing process the polymer is solidified and processed to form a pelletized or granular resin or bead. Applicants recognize the polymer may be solidified and processed to form resin or bead first, followed by devolatilization. The resin is then fed to a drying process (16) by conveyance means (15). Within the drying process (16) moisture is removed as a vapor through pipeline (17). The dried lactide polymer resin leaves the drying process (16) by a conveyance means (18) and is fed to a melt-processing apparatus (19). Within the melt-processing apparatus (19) the resin is converted to a useful article as disclosed above. The useful article leaves the melt-processing apparatus (19) through a conveyance means (20).

The following examples further detail advantages of the system disclosed herein:

#### Example 1

##### Melt Spinning of Poly(lactide)

Melt spinning of poly(lactide) having a weight average molecular weight of 140,000, a residual lactide content of about 1.1% and an original lactide mixture of

about 7% by weight meso-lactide was performed on a 13 mm. single screw extruder with a gear pump and fitted with a 7 hole multifilament spinning head. The hole diameter was 0.4 mm. The spinline length, the distance from the spinning head to the take-up roll, was 1.7 meters. Polymer throughput was 1 g/min/hole. Filaments were drawn down by drawing through a circular aspirator which makes use of high velocity air to apply a force downward on the fibers. Post drawing of the fibers was also done on a draw stand or heated godet.

The process conditions were varied to find conditions under which fibers could be made from poly(lactide). Extrusion temperatures were varied from 150 to 170°C and the take up velocity was varied from 500 to 6,000 meters/min. Fiber diameters were measured and are shown in Table 1 for the various fiber spinning conditions. With a microscope equipped with a light polarizer, birefringence was measured to assess the extent of polymer orientation within the fiber as a function of spinning conditions. Table 1 shows birefringence as a function of take-up velocity and fiber diameter as a function of take-up velocity respectively.

25

Table 1

	<u>Take-up Velocity (meters/min)</u>	<u>Extrusion Temperature (°C)</u>	<u>Fiber Diameter (microns)</u>	<u>Birefringence x1000</u>
30	2674	170	19.0	13.84
	6179	160	12.5	15.84
	4656	160	14.4	12.71
	3177	160	17.6	9.09
	4656	150	14.4	14.94
35	3421	150	16.8	8.04
	3117	150	17.6	11.82
	478	150	45.0	0.91

40

Fibers collected at a take-up velocity of 478 meters/min were post drawn on a heated godet. This



apparatus is a series of rolls, including an unwind roll on the front and a take-up roll on the back. With the take up roll rotating faster than the unwind roll, the fiber is stretched. The rolls in between the unwind and take-up are heated to a temperature of 50°C to soften the polymer and allow the fiber to be drawn. Measuring fiber diameter allows calculation of the draw ratio and birefringence relates to the degree of orientation of the polymer chains. Table 2 summarizes the drawing data. The data illustrates it is possible to postdraw the fibers to increase the orientation of the fibers.

Table 2

	<u>Initial Diameter</u>	<u>Final Diameter</u>	<u>Draw Ratio</u>	<u>Birefringence x 1000</u>
20	45.00	26.00	3.00	16.64
	45.00	25.10	3.18	19.73
	45.00	24.80	3.32	21.94
25	45.00	24.00	3.50	19.58

Example 2

Properties of Poly(lactide) Melt Spun Fibers.

In an apparatus similar to that used in Example 1, poly(lactide) having a weight average molecular weight of about 100,000, a residual lactide content of less than about 1% and an original lactide mixture of about 10% by weight of meso-lactide was melt spun into a fiber. The optical composition was such that upon annealing, (the sample was held at 100°C for 90 minutes, the oven was turned off and was allowed to cool to room temperature), the polymer exhibited an endothermic melt peak with a peak temperature of 140°C with an endotherm of 36.1 joules/gram.

- The poly(lactide) fibers were post drawn as in Example 1. The thermal and mechanical properties are shown in Table 3. The results compare favorably to standard fiber resins such as polypropylene and nylon.
- 5 The elongation and modulus compare favorably to commercial fibers. Further, poly(lactide) exhibited an affinity to crystallize under the conditions of fiber spinning.

Table 3

<u>Properties</u>	<u>Resin</u>	<u>As-Spun</u>	<u>Drawn</u>	<u>Polyprop.</u>	<u>Nylon 6,6</u>
5 Melt Temp (°C)	133	140	140	170	265
Heat of Fusion (J/g)	2.4	14.2	26.4	105	xxxxx
Denier (g/9000m)	xxxxx	162	57	xxxxx	xxxxx
Tenacity (g/den)	xxxxx	0.97	2.75	6.5	5.4
Break Elongation	xxxxx	165%	38%	34%	20%
10 Young's Modulus (g/den)	xxxxx	22	44	68	34

Example 3Melt Blown Fabrics from Poly(lactide)

On a six inch melt blown nonwoven line equipped with a single screw extruder, poly(lactide) of a weight average molecular weight of about 80,000, a residual lactide content of about 0.6%, an original lactide mixture of about 9% by weight of meso-lactide and a water content of about 70 ppm was converted into melt blown nonwoven webs. This process involves feeding resin pellets into a feeding hopper of an extruder having a one inch single screw and extruding molten polymer through a die containing many small holes out of which emerges small diameter fiber. The fiber diameter is attenuated at the die as the fiber emerges using high velocity hot air. Three inches from the die exit is a rotating collection drum on which the fibrous web is deposited and conveyed to a wind up spool. The melt blown line is of standard design as in Malkan et al. (Nonwovens: An Advanced Tutorial, TAPPI press, Atlanta, 1989, pp 101-129). The die used had 121 holes with a diameter of 0.020 inch per hole.

Conditions were varied to find conditions under which poly(lactide) could be made into a useful nonwoven fabric. The die temperature was varied from 380 to 480°F, the air temperature was varied from 458 to 500°F, the die-to-collector distance varied from 6 to 14 inches and the air velocity varied from approximately 12 to 18 cu-ft/min/inch web.

The resultant poly(lactide) webs were tested for performance using standard tests for melt blown fabrics. The basic weight of all webs was 1 oz/sq-yd. Fiber diameter and fiber diameter variability were measured using a scanning electronic microscope. Tensile stress-strain properties were measured using ASTM method D-1682-64. Bursting strength was measured using the Mullen Bursting Tester and ASTM method D-3387. Filtration efficiency was assessed using an aerosol having 0.1 micron sodium chloride

particles. The filtration test involved making a 20 gram/liter NaCl solution and making an aerosol of the solution with a concentration of 100 milligram per cubic meter. The aerosol was thereafter passed through the

5 fabric at 31 liters/minute. Sensors were placed both upstream and downstream of the fabric, with the difference reflecting the amount remaining in the filter. Air permeability, another feature important to filtration, was measured according to ASTM D737-75 and reported as cubic

10 feet of air per square feet of fabric per minute. All of these performance measures were compared to standard polypropylene fabrics. The data illustrates poly(lactide) processes as well as polypropylene. Poly(lactide) is capable of forming fine or small diameter fibers. Fibers

15 having diameters of less than about 5  $\mu\text{m}$  are shown. Further, poly(lactide) nonwoven webs have a high filtration efficacy as well as good air permeability. The results are shown in Table 4.

Table 4

## Conditions:

5	<u>Sample</u>	<u>1</u>	<u>2</u>	<u>3</u>	<u>4</u>	<u>5</u>	<u>6</u>	<u>7</u>	<u>8</u>	<u>typical PP</u>
	Die temp. °F	380	395	395	395	395	395	395	395	480
10	Air temp. °F	446	446	446	446	446	460	460	458	500
	DCD inches	10	10	10	6	14	10	14	10	12
15	Air Valve rate	40%	40%	50%	50%	50%	60%	60%	55%	40%

## Property:

20	<u>Sample</u>	<u>1</u>	<u>2</u>	<u>3</u>	<u>4</u>	<u>5</u>	<u>6</u>	<u>7</u>	<u>8</u>	<u>typical PP</u>
	Air Permeabil. ft <sup>3</sup> /ft <sup>2</sup> /min	271	247	175	90	227	103	137	149	50-100
25	Bursting Strength, psi	8.3	9.3	9.6	7.6	8.6	8.8	10.6	10.0	6-10
	Filtration Eff. %	38.9	37.3	43.2	60.0	47.7	65.3	59.0	47.0	25-60
30	Peak Load, lb/in.	2.10	2.15	2.30	4.77	1.00	3.26	1.50	2.80	0.8-3.5
	Peak Elongation, %	3.10	2.80	3.70	3.90	2.50	5.10	3.00	4.40	10-30
35	Av. Fiber Dia. μm	3.83	xxxx	2.88	xxxx	xxxx	xxxx	3.41	xxxx	2-4
	C.V. % Fiber Dia.	32.61	xxxx	37.77	xxxx	xxxx	xxxx	37.03	xxxx	25-40

Example 4Melt Blow Nonwovens made from Poly(lactide).

Melt blown fabrics were made with poly(lactide) using the same equipment and procedure as in Example 3. The  
5 extrusion temperature was 320°F, screw speed was 8 rpm, die temperature was 315°F, air temperature and air velocity were at 400°F and 12 cu ft/min/inch web respectively. Die-to-collector distance was 13 inches.

The poly(lactide) used in this test had a weight  
10 average molecular weight of about 66,000, a residual lactide concentration of about 1.3% and an original lactide mixture of about 9% by weight of meso-lactide. This lower molecular weight resulted in softer nonwoven fabrics than Example 3 and had good hand. Fiber diameters were measured  
15 and found to be 11.57  $\mu$ m. Other tests done on this fabric was the air permeability test having a value of 4.26, bursting strength having a value of 5.4, and filtration efficiency having a value of 14.0%.

Example 5

20

Anti-Blocking Agents

Two injection molded disks, 2.5 inch diameter, were placed together with a 94 gram weight on top and held at 50°C for 24 hours. The disks had the following agents compounded therein. The disks were then cooled to room  
25 temperature and pulled apart by hand and ranked for blocking characteristics (considerable, slight and none). The following are the results:

Table 5AGENTS

5	Poly(lactide) control	considerable
	22% wheat gluten	none
	10% wheat gluten	slight
	22% pecan shell	none
10	15% pecan shell	slight
	23% wollastonite	slight
	28% Ultratalc 609	none
15	23% Ultratalc 609	none
	28% Microtuff F talc	slight
	22% Microtuff F talc	slight
20	14% Microtuff F talc	slight
	2% Microtuff F talc	considerable

Example 6

25

Plasticizer Agents

Dried pellets of devolatilized poly(lactide) were processed in a twin screw extruder to allow compounding of various plasticizing agents. The strands leaving the extruder were cooled in a water trough and chopped into pellets. Samples of the pellets were heated at 20°C/minute to 200°C in a DSC apparatus, held at 200°C for 2 minutes and rapidly cooled to quench the samples. The quenched samples were then reheated in the DSC apparatus increasing at 20°C/minute to determine the glass transition temperature. These samples were compared to a polymer with no plasticizer. The effect of the plasticizer on the glass transition temperature is shown in the table below. Glass transition temperatures are taken at the mid-point of the transition.



Table 6

	<u>SAMPLE</u>	<u>T<sub>g</sub>(C)</u>	<u>Change in T<sub>g</sub>/wt. percent additive</u>
	Control	54.8	---
5	8% Dioctyl adipate	35.0	2.5
	Control+40% silica	54.5	---
	Control+40% silica+ 5% dioctyl adipate	36.0	3.7
10	Control	54.6	---
	6% Citroflex A-4*	42.6	2.0
	12% Citroflex A-4	31.4	1.9
15	Control	59.3	---
	1.6% Citroflex A-4	56.3	1.9
	2.9% Citroflex A-4	53.1	2.1
	Control	58.4	---
20	2.1% Citroflex A-4	56.1	1.1
	3.4% Citroflex A-4	50.5	2.3
	Control	61.6	---
	18.6% Citroflex A-2	54.7	0.4
25	13.1% Citroflex B-6	52.4	0.7
	12.6% Citroflex A-6	53.8	0.6

\*Citroflex is a registered trademark of Morflex, Inc.,  
 30 Greensboro, NC. A-4 is the designation of acetyltri-n-butyl citrate. A-2 is the designation of acetyltriethyl citrate, A-6 is the designation of acetyltri-n-hexyl citrate, and B-6 is the designation of n-butyryltri-n-hexyl citrate.

35 These results show the effectiveness of these plasticizers in reducing the glass transition temperature of poly(lactide).

The procedure above was tried using corn oil as a plasticizer. Visual observation showed the corn oil to be  
 40 not compatible, forming a film on the surface. Corn oil and mineral oil were both not effective as a primary plasticizer with poly(lactide). They may still be useful as a secondary plasticizer, in combination with a compatible primary plasticizer.

Example 7Lactide and Poly(lactide) Equilibrium Concentrations

Experiments were conducted to determine the equilibrium concentration of lactide and poly(lactide) at different temperatures. In these experiments a sample of lactide was polymerized in the presence of a catalyst (tin (II) bis(2-ethyl hexanoate)) and held at a fixed temperature for 18 hours or greater. Beyond this time the residual monomer concentration is believed essentially constant. The content of residual monomer was determined by GPC analysis. GPC analysis was conducted with an Ultrastyrigel® column from Waters Chromatography. The mobile phase was chloroform. A refractive index detector with molecular weight calibration using polystyrene standards was used. The GPC temperature was 35°C. Data analysis was completed using the software package Baseline, model 810, version 3.31.

The results of tests conducted on several samples at various temperatures are summarized in the graph of Fig. 2 as indicated by X's on such graph. Also plotted on the graph of Fig. 2 are data points cited in A. Duda and S. Penczek, Macromolecules, vol. 23, pp. 1636-1639 (1990) as indicated by circles on the graph. As can be seen from the graph of Fig. 2, the equilibrium concentration, and thus the driving force behind the depolymerization of poly(lactide) to form lactide, increases dramatically with increased temperature. Thus, melt-processing at elevated temperatures results in degradation of the lactide polymer to form lactide on the basis of equilibrium alone. For example, lactide concentrations below about 2% cannot be directly obtained at temperatures of 140°C or above due to the identified equilibrium relationship between lactide and poly(lactide).

Example 8Lactide Polymerization in the Presence  
of a Solid Supported Catalyst5     Tin (II) Oxide

24 grams of L-lactide (melting point about 97°C) and 6 grams of D,L-lactide (for the purposes of this invention, D,L-lactide has a melting point of about 126°C) were combined in a round bottom flask with 0.033 grams of Tin  
10 (II) oxide, as a fine powder. This corresponds to the catalyst level of 852:1, molar ratio lactide to tin. The flask was then purged with dry nitrogen 5 times. This was lowered into an oil bath at 160°C with magnetic stirring. Polymerization time was 8 hours.

15     Amberlyst 36

24 grams of L-lactide and 6 grams of D,L-lactide were combined in a round bottom flask with 1.06 grams of Amberlyst 36 resin beads. The flask was purged 5 times with dry nitrogen. The flask was lowered into an oil bath  
20 at 140°C with magnetic stirring. Polymerization time was 8 hours. The resin had a stated proton content of 1 meq/gram dry weight resin. The resin was prepared by rinsing 2 times with 10 volumes dry methanol, then dried for several hours under high vacuum for several hours at 40°C.

25     The polymerization results are shown below:

TABLE 7

	<u>Sample</u>	<u>Mn</u>	<u>Mw</u>	<u>PDI</u>	<u>% Conversion</u>
30	Tin (II) Oxide	77,228	103,161	1.34	54.0
	Amberlyst	1,112	1,498	1.34	73.5

35

Example 9Molecular Weight Relationship to Physical  
Properties of Lactide Polymers

Poly(lactide) samples with various molecular weights  
5 and optical compositions were prepared by polymerizing  
blends of L-lactide and meso-lactide at 180°C under  
nitrogen in a 1-gallon sealed reactor. Tin(II) bis(2-ethyl  
hexanoate) catalyst was added at a monomer-to-catalyst  
ratio of 10,000:1. After about 1 hour the molten polymer  
10 was drained from the reactor using nitrogen pressure. The  
sample was poured into a pan and placed in a vacuum oven at  
about 160°C for about 4 hours to bring the reaction to near  
equilibrium levels.

Portions of the samples were then dried under vacuum  
15 and processed in an injection molding apparatus (New  
Britain 75 from New Britain Machine Co.) to produce  
standard test bars for physical property testing. The  
results of physical property testing are shown in the  
following Table 8. The physical property tests were made  
20 according to ASTM methods D 638, D 256, and D 790. The  
reported results are the averages of several tests.

Samples of the test bars after injection molding were  
analyzed by GPC for molecular weight. Other portions of  
the test bars were reground and tested in a capillary  
25 viscometer to determine the melt-viscosity. These results  
are also included in Table 8.

Statistical analysis of the data revealed no  
correlations which were statistically significant between  
either optical composition or molecular weight and the  
30 mechanical properties of modulus, tensile strength,  
percentage elongation at break, notched Izod impact  
strength, flexural modulus, or flexural strength. The  
independence of these properties on molecular weight  
indicates that all of these samples were above a  
35 "threshold" molecular weight required to achieve the  
intrinsic properties of the polymer in a preferred

composition.

The viscosity data show significant correlations with molecular weight. This dependence documents the practical limitation and necessity of controlling polymer molecular weight below an upper limit at which it is impractical to melt-process the polymer. At high molecular weight, high viscosity prevents processing by standard melt-processing equipment. Increases in temperature to reduce viscosity dramatically increase polymer degradation and lactide formation which is also unacceptable.

TABLE 8

Sample I.D.	Meso Lactide In Blend, Wt%	Molecular Weight After Injection Weight	Viscosity at 173°C (Pa·S)		
			Final IV (dl/g)	Shear Rate 100 S <sup>-1</sup>	Shear Rate 1000 S <sup>-1</sup>
6	40	41000	0.86	5.5	2.9
5	10	54000	0.88	10.4	7.2
4	20	59000	0.91	10.4	7.2
8	10	64000	1.02	15.7	10.0
9	40	68000	0.97	12.6	8.1
7	20	Dataproducts LZR-1230 *M&G* /HGCCDALZR124.PRSies of Injection Molded Samples			

Sample I.D.	Modulus MPa	Tensile Strength (Yld) PSI	% Elongation at Break	IZOD Impact ft · lb./in	Flexural Modulus MPa	Flexural Strength PSI
6	0.55	6600	3.3	0.39	0.53	11300
5	0.56	7800	3.5	0.46	0.54	12500
4	0.56	7600	3.9	0.32	0.53	12500
8	0.55	7700	3.4	0.47	0.53	12400
9	0.59	6700	3.1	0.42	0.52	10600
7	0.56	7400	3.3	0.45	0.51	12400
10	0.55	6700	3.0	0.47	0.52	9900

#### Example 10

##### Effect of Residual Catalyst on Polymer Degradation

Polymer samples were prepared at four levels of catalyst, corresponding to monomer to catalyst molar ratios of 5,000:1, 10,000:1, 20,000:1, and 40,000:1. The catalyst utilized was tin (II) bis(2-ethyl hexanoate). These samples were then subjected to heating in a TGA apparatus (TA Instruments, Inc., model 951 thermogravimetric analyzer with a DuPont 9900 computer support system) with a nitrogen purge. Isothermal conditions of 200°C for 20 minutes were used. The samples were then analyzed by GPC with a viscosity-based detector and a universal calibration curve to determine the extent of breakdown in molecular weight.

The GPC apparatus for this test was a Viscotek Model 200 GPC and a Phenomenex column. The TGA analysis typically resulted in about a 5% loss in weight and molecular weight drops of 0 to 70%.

5 The number average molecular weights were converted to a milliequivalent per kilogram basis (1,000,000/Mn) in order to calculate a rate of chain scission events. The results below represent averages of 2-4 replicates on each of the four samples.

10

TABLE 9

	Catalyst level (monomer/catalyst)	Scission Rate (meq/kg*min)
15	5,000	1.33
	10,000	0.62
	20,000	0.44
20	40,000	0.12

The rate of chain scission was directly proportional to the residual catalyst level, demonstrating the detrimental effect of catalyst activity on melt-stability under conditions similar to melt-processing. This instability, however, is distinguished from the instability due to the equilibrium relationship between lactide and poly(lactide) detailed in Example 7, in that loss of molecular weight due to catalytic depolymerization by chain scission is evident.

30

EXAMPLE 11Catalyst Deactivation Experiment

Two runs were made in a laboratory Parr reactor. Lactide feed was 80% L-lactide and 20% D,L-lactide.

35 Molecular weight was controlled by adding a small quantity of lactic acid, the target molecular weight was 80,000 Mn.

Lactide was charged to the reactor as a dry mix, the reactor was purged 5 times with nitrogen, and heated up to 180°C. At this point catalyst (5000:1 initial monomer to

catalyst molar ratio, Fascat® 2003) was charged through a port in the top of the reactor. The reaction was allowed to proceed for 70 minutes at 180°C, with mechanical agitation. Conversion at this point was 93-94%, close to the equilibrium value at 180°C of 96% poly(lactide) from Figure 2. This point is considered t-zero, designating the completion of the polymerization reaction and the beginning of the mixing time.

In the control experiment, a sample was taken and the mixture was held at temperature with continued agitation. Samples were taken periodically through a port in the reactor bottom. After 4 hours the reactor was drained.

In the example experiment, a sample was taken and 0.25 weight % of a metal deactivator (Irganox® MD 1024®) was added through the catalyst addition port. The mixture was held at temperature with continued agitation and samples were withdrawn periodically. The reactor was drained after 4 hours.

GPC analysis (utilizing the method of Example 7) for these samples was divided into three parts: polymer with molecular weight over 4,000 (for which the Mn and Mw numbers are reported), the percent oligomers (comprising the region with molecular weight greater than lactide but less than 4,000, as distinguished from oligomers as defined by Loomis to include only oligomers up to a molecular weight of 450), and percent lactide (residual monomer). The structure of the oligomers was not certain, but it is believed they were primarily cyclic structures. It is also believed that the metal deactivator, if unreacted, will elute with the oligomer fraction. Quantification of the oligomer fraction is difficult, because the GPC trace is near the baseline in this region.

The analysis of the polymer samples as withdrawn from the reactor at various time intervals for the control and experimental compositions are shown below in Table 10.



TABLE 10

	Control	Mn	Mw	% Polymer	% Oligomer	% Monomer
5	t-zero	67,100	119,500	94	0	6.0
	0.5 hr	62,500	119,000	95	0.7	3.9
	1.0 hr	61,500	116,100	96	0	3.6
	1.5 hr	56,000	111,600	95	1.5	3.3
	2.0 hr	57,600	110,900	96	0.9	3.1
10	4.0 hr	51,400	105,400	94	3.3	3.1

	Test	Mn	Mw	% Polymer	% Oligomer	% Monomer
15	t-zero	63,200	110,700	93	3.5	3.8
	0.5 hr	52,100	108,600	92	4.6	2.9
	1.0 hr	52,700	109,200	92	4.9	2.8
	1.5 hr	53,400	107,200	93	4.0	3.1
	2.0 hr	59,700	111,100	94	0.6	5.8
20	4.0 hr	51,200	107,300	91	6.1	3.3

The samples were then ground and placed in a 120°C oven under vacuum (pressure 0.1 inch Hg) for 14 hours.

25 Sample analyses after this treatment are shown below in Table 11.

TABLE 11

	Control	Mn	Mw	% Polymer	% Oligomer	% Monomer
30	t-zero	45,500	88,500	98	2.2	0.0
	0.5 hr	45,000	88,700	98	2.0	0.0
	1.0 hr	43,900	87,200	98	2.0	0.0
	1.5 hr	42,600	84,000	98	2.2	0.0
35	2.0 hr	42,000	85,200	97	3.2	0.0
	4.0 hr	41,900	82,800	98	2.0	0.0

	Test	Mn	Mw	% Polymer	% Oligomer	% Monomer
40	t-zero	39,300	76,700	96	4.0	0.0
	0.5 hr	43,900	85,100	98	2.4	0.0
	1.0 hr	55,300	98,600	96	3.8	0.0
	1.5 hr	48,400	96,200	95	4.5	0.0
	2.0 hr	48,900	101,900	95	5.0	0.0
45	4.0	50,600	101,900	94	5.6	0.0

In all cases the polymer was completely devolatilized (0.0% residual lactide monomer). The data also clearly show that the metal deactivator reduced the degradation of polymer during the devolatilization step (as indicated by the greater loss in Mn for the control samples from Table 9 to Table 10 versus the Test samples). One hour of mixing appears to be long enough to develop most of the benefit.

The samples were stored at room temperature under nitrogen for about 1 week and reanalyzed, as shown below in Table 12.

TABLE 12

	Control	Mn	Mw	% Polymer	% Oligomer	% Monomer
15	t-zero	33,500	71,000	100	0.1	0.0
	0.5 hr	43,400	95,800	99	1.0	0.0
	1.0 hr	44,900	96,300	100	0.1	0.0
	1.5 hr	45,900	95,000	100	0.0	0.0
20	2.0 hr	45,900	94,100	100	0.2	0.0
	4.0 hr	43,100	90,100	99	1.3	0.0
	Test	Mn	Mw	% Polymer	% Oligomer	% Monomer
25	t-zero	44,600	84,900	100	0.0	0.0
	0.5 hr	45,300	90,600	99	1.2	0.0
	1.0 hr	47,800	100,000	98	2.4	0.0
	1.5 hr	46,600	98,900	96	3.5	0.0
30	4.0	57,700	110,200	96	4.0	0.3

Equilibrium lactide levels are estimated to be less than 0.2 weight % at room temperature. Consistent with that, essentially no lactide was observed in any of the samples (detection limit about 0.1 weight %). The oligomer content in the non-stabilized samples declined and some increase in molecular weight was noted, perhaps due to reincorporation of the (cyclic) oligomers into the polymer. The oligomer depletion reaction was inhibited in the stabilized polymers, with the extent of inhibition dependent on the length of time that the additive was mixed.

The samples were then reheated to 180°C in sealed vials

and held for one hour as a simulation of melt-processing. Analysis of the samples after the heat treatment is given below in Table 13.

TABLE 13

Control	Mn	Mw	% Polymer	% Oligomer	% Monomer
t-zero	23,900	60,000	88	8.4	4.0
0.5 hr	23,900	59,600	90	7.7	2.7
1.0 hr	23,700	58,800	88	9.3	2.7
1.5 hr	24,700	58,000	86	10.0	3.8
2.0 hr	26,100	56,400	90	6.8	2.7
4.0 hr	24,800	58,700	92	6.6	1.9

Test	Mn	Mw	% Polymer	% Oligomer	% Monomer
t-zero	33,900	64,300	95	2.2	3.1
0.5 hr	17,900	34,600	94	4.8	1.7
1.0 hr	21,200	42,900	94	4.6	1.8
1.5 hr	29,200	56,900	98	0.5	1.8
2.0 hr	missing				
4.0 hr	35,700	71,400	95	3.7	1.7

The data for molecular weight show that if the metal deactivator is not mixed into the system long enough then it can have a detrimental impact on stability in the melt. The samples Dataproducts LZR-1230 \*M&G\* /HGCDALZR124.PRSight alone. More importantly, the metal deactivator samples show significantly less lactide reformation than the control samples. This effect is gained even in the samples which were mixed for only 0.5 hour. The metals deactivated samples averaged only 1.8% lactide after one hour at 180°C, compared to an average of 3.0% lactide for the controls. The equilibrium level at 180°C is about 3.6% from Figure 2. Thus, the use of metal deactivators can reduce the troublesome reformation of lactide during melt-processing of the finished polymer.

Example 12Effect of Increased Polymerization Temperature  
on Polymer Characteristics

L-lactide (Boeringer Ingleheim, S-grade) was used as  
5 received, meso-lactide (PURAC) was purified by distillation  
to remove traces of D- and L-lactide. The melting point of  
the purified meso-lactide was 54°C. Lactide mixtures were  
made up to the following ratios: 100% L-lactide, 90/10 L-  
lactide/meso-lactide, 70/30 L-lactide/meso-lactide, 50/50  
10 L-lactide/meso-lactide, and 100% meso-lactide. Catalyst  
level was 2,500:1 molar ratio of initial monomer to tin  
with the tin being tin(II) bis (2-ethyl hexanoate) (Fascat®  
9002). Lactic acid was added as a molecular weight control  
agent to target a number average molecular weight of 50,000  
15 (the same amount was added to all samples). Polymerization  
times were estimated to obtain conversions of 50% and 90%.  
For 120°C this was 4 hours and 16 hours, respectively. For  
180°C these times were 10 minutes and 50 minutes,  
respectively. Below in Table 9 are the GPC results (method  
20 of Example 7) of tests on the polymer samples produced by  
this procedure.

TABLE 14

	L/meso	Temp	Mn	Mw	PDI	ICnv
5	100% L	120°C	31,014	33,774	1.09	53.2
			45,864	52,574	1.15	87.1
	100% L	180°C	27,785	32,432	1.17	46.7
			56,839	98,125	1.73	93.3
10	90/10	120°C	34,541	38,586	1.12	62.3
			29,222	34,466	1.18	89.3
	90/10	180°C	31,632	35,713	1.13	48.5
			57,925	110,841	1.91	94.8
15	70/30	120°C	41,211	45,222	1.10	60.1
			58,284	71,257	1.22	89.1
20	70/30	180°C	32,292	37,401	1.16	53.8
			51,245	107,698	2.10	96.5
	50/50	120°C	15,888	17,969	1.13	57.8
			25,539	31,834	1.25	90.6
25	50/50	180°C	34,375	42,018	1.22	62.5
			44,590	98,028	2.20	95.5
	100% meso	120°C	33,571	40,635	1.21	73.4
			45,237	68,142	1.51	94.3
30	100% meso	180°C	30,976	42,987	1.39	67.6
			40,038	83,815	2.09	96.6

35

The results show that the ultimate number average molecular weight was not significantly affected by the temperature of polymerization, with an average of 41,000 at 120°C and 50,000 at 180°C. This implies that each lactic acid molecule initiates about one polymer chain, regardless of temperature. The ultimate weight average molecular weight is, however, significantly affected by temperature. At 120°C the weight average molecular weight averaged 52,000 and at 180°C the average was 100,000. This is believed to be due to a relative increase in the rate of transesterification at 180°C. The polydispersity index (PDI) at high conversion also reflects this, averaging 1.3

at 120°C and 2.0 at 180°C. It is believed these differences would have a significant effect on the melt-processing characteristics of the polymer, with the higher weight average molecular weight of the polymer produced at 180°C expected to translate into better melt strength and processability.

These experiments show that polymerization at a higher temperature results in a polymer that is characteristically different. Further, the glass transition temperature for the samples polymerized at higher temperature is higher.

### Example 13

#### Experiments with Stabilizing Agents and Metal Deactivators

##### Test 1

Conditions: vial polymerization, (Lactide is melted under a nitrogen-purged atmosphere in a round bottom flask with stirring. Catalyst and additives are added and aliquots of the mixtures are pipetted into silanized glass vials. Typically 5-10 grams of reaction mixture are used in a 16 ml. vial. The vials are tightly capped and placed into a preheated oil bath.) 10,000:1 molar ratio of lactide-to-tin, tin(II) bis(2-ethyl hexanoate) catalyst, 0.2 wt% Ultrinox®626 in tetrahydrofuran (THF). 180°C. Time was 90 minutes.

The control with tin only polymerized to 84% conversion and reached a MWn of 31,700. The example with tin and Ultrinox® polymerized to 83% conversion and reached a number average molecular weight (MWn) of 39,800; an increase of 26% over the control.

The control sample turned light yellow, the sample with stabilizer remained colorless.

Test 2

Conditions: vial polymerization, 5000:1 molar ratio of lactide to tin, tin(II) bis(2-ethyl hexanoate) catalyst, 0.25 wt % Ultrinox<sup>®</sup> 626 (in THF). 180°C. Time was 60 minutes. Lactide was used from the above described Gruber et al. process.

The control with tin alone polymerized to 67% conversion and reached a MWn of 62,900. The example with tin and Ultrinox<sup>®</sup> polymerized to 66% conversion and reached a MWn of 75800; an increase of 21% over the control.

A second example with tin(II) bis(2-ethyl hexanoate), Ultrinox<sup>®</sup>, and 0.50% of Irganox<sup>®</sup> 1076, which is a phenolic antioxidant, polymerized to 66% conversion and reached a number average molecular weight (MWn) of 74500; an increase of 18% over the control.

All samples were a dark yellow color, although the samples with stabilizer had a slightly lower absorbance at 300 nm.

Test 3

Conditions: vial polymerization, 10,000:1 molar ratio of lactide to tin, tin(II) bis(2-ethyl hexanoate) catalyst, 180°C, 80% L-lactide and 20% D,L-lactide purchased from Henley and Aldrich, respectively. Lactic acid was added to control molecular weight to about 75,000 at full conversion. One sample included 0.25% Ultrinox<sup>®</sup> 626 phosphite stabilizer, one included 0.25% Irganox<sup>®</sup> 1076 antioxidant, and one control sample.

Samples were taken at various times and analyzed by GPC for conversion and molecular weight (the method of Example 7). The results are summarized in Table 15 below.

TABLE 15

	Time (hrs)	Control		Irganox®		Ultranox®	
		Mn	%conv	Mn	%conv	Mn	%conv
5	1	31,000	46	35,900	41	66,500	61
	2	45,400	74	56,800	74	102,700	83
	4	69,600	93	74,100	93	97,200	91
10	11	52,900	95	60,700	95	71,500	94

The sample with phosphite stabilizer polymerized faster, shown by the higher conversion at 1 and 2 hours, and went to a higher molecular weight than the control or the sample with Irganox®. The phosphite stabilized sample had a molecular weight more than 30% higher than the control for all time periods.

Test 4

The experiment above was repeated to compare the control to the phosphite-stabilized polymer, as summarized in Table 16 below.

TABLE 16

	Time (hrs)	Control		Ultranox®	
		Mn	%conv	Mn	%conv
25	1	36,600	37	71,500	59
	2	51,700	70	95,200	85
	4	64,400	91	103,700	94
30	8	58,100	96	95,700	94

The sample with phosphite stabilizer again polymerized faster and went to a higher molecular weight than the non-stabilized sample. The phosphite stabilized sample had a molecular weight more than 60% higher than the control for all time periods.

Test 5

Conditions: vial polymerization, 5,000:1 molar ratio of lactide to tin, tin(II) bis(2-ethyl hexanoate) catalyst, 180°C, 80% L-lactide and 20% D,L-lactide purchased from Henley and Aldrich. Lactic acid was added to control



number average molecular weight to an estimated 80,000 at full conversion. One sample was run with 0.25% Ultrinox® 626 phosphite stabilizer, one with 0.25% Irganox® 1076 antioxidant, and one control sample.

- 5 Samples taken at various times and analyzed by GPC (the method of Example 1) for conversion and molecular weight. The results are tabulated in Table 17 below.

TABLE 17

Time (hrs)	Control		Irganox®		Ultrinox®	
	Mn	%conv	Mn	%conv	Mn	%conv
1	83,600	76	121,900	83	162,300	87
4	74,400	93	104,300	95	123,900	96
24	40,200	96	52,000	96	96,900	97
48	34,200	97	30,400	96	56,500	96
72	25,000	96	22,400	96	69,500	96

- 20 The phosphite-stabilized sample had a molecular weight more than 60% higher than the control for all time periods. After 72 hours it had a molecular weight 2.8 times higher than the control. The sample with antioxidant showed an initial increase in molecular weight, relative to the control, but the effect disappeared after 48 hours.

25 The phosphite stabilized sample was significantly lighter in color than the control or the antioxidant treated sample.

### 30 Test 6

- Conditions: vial polymerization, 5000:1 molar ratio of lactide to tin, tin(II) bis(2-ethyl hexanoate) catalyst, 0.25 wt % Ultrinox®626 (in THF). 180°C. Time was two hours. Gruber et al. process lactide washed with isopropyl alcohol was used.

The control with tin alone polymerized to 95% conversion and reached a number average molecular weight of 118,000. The example with tin and Ultrinox® polymerized to 93% conversion and reached a number average molecular

weight of 151,000, an increase of 28% over the control.

Test 7

Conditions: vial polymerization at 180°C. 5000:1  
molar ratio of lactide to tin, tin(II) bis(2-ethyl  
5 hexanoate) catalyst. Lactide was 80% L-lactide and 20%  
D,L-lactide, purchased from Henley and from Aldrich.  
Lactic acid was added to target the molecular weight to an  
Mn of 80,000. All stabilizers were added at 0.25 weight%.  
Molecular weight (number average) was determined for  
10 samples pulled at 3 hours, while rate constants were based  
on samples pulled at 1 hour. The results of these  
screening tests on many stabilizing agents following the  
above procedure are detailed below in Table 18. Product  
designations in Table 18 are tradenames or registered  
15 trademarks.

57

TABLE 18

	<u>Sample</u>	<u>MWn</u>	<u>% Conversion</u>	<u>Relative Rate</u>
5	Control 1	65,000	95.9	90
	Control 2	85,000	95.9	100
	Control 3	76,000	96.6	100
	Control 4	69,000	96.2	100
	Control 5	74,000	96.8	110
10	Control 6	70,000	97.2	110

PHOSPHITES

15	Ultrinox 626	(GE)	103,000	96.8	100
	Weston TDP	(GE)	64,000	70.0	60
	Weston PDDP	(GE)	67,000	76.7	60
	Weston PNPG	(GE)	92,000	94.1	100
	Irgafos 168	(Ciba-Geigy)	95,000	95.3	120
20	Weston 618	(GE)	99,000	95.1	100
	Sandostab P-EPQ	(Sandoz)	108,000	94.7	110
	Weston TNPP	(GE)	88,000	97.9	130

25 PHENOLIC ANTIOXIDANTS

	Irganox 1010	(Ciba-Geigy)	95,000	97.5	110
	Cyanox 1790	(Cyanamid)	98,000	96.9	120
	BHT		87,000	96.5	130
30	Irganox 1076	(Ciba-Geigy)	121,000	97.8	130
	Topanol CA	(ICI)	84,000	96.6	160

AMINES

35	Tinuvin 123	(Ciba-Geigy)	65,000	94.8	70
	Tinuvin 622	(Ciba-Geigy)	82,000	95.7	80
	Naugard 445	(Uniroyal)	93,000	98.2	120

40

THIOETHER

	Mark 2140	(Witco)	77,000	97.0	120
--	-----------	---------	--------	------	-----

45

METAL DEACTIVATORS

	Irganox MD1024	(Ciba-Geigy)	34,000	65.7	10
	Naugard XL-1	(Uniroyal)	91,000	95.8	110

Note, that with a few exceptions, the phosphites and the phenolic antioxidants provide increased molecular weight with no reduction in polymerization rate. Of the amines, only Naugard® 445 provided stabilization without a rate decrease. The metal deactivators are expected to deactivate the catalyst, as was observed for Irganox® MD1024. The Naugard® XL-1 did not accomplish deactivation.

#### Example 14

##### 10 Polymer Melt Stability as a Function of Moisture Content

Lactide, produced and purified in a continuous (Gruber et al.) process, was fed at a rate of 3 kg/hr to a continuous polymerization pilot plant. Catalyst was added with a metering pump at the rate of 1 part catalyst to 5000 parts lactide on a molar basis. The reaction system was blanketed with nitrogen. The reactor vessels consist of two continuous stirred tank reactors (CSTR) in series. The first had a 1-gallon capacity and the second had a 5-gallon capacity. The reactors were run 60-80% liquid filled and at 170-180°C. Polymer melt pumps moved the liquid from CSTR 1 to CSTR 2, and from CSTR 2 through a die into a cooling water trough. The polymer strand thus produced was pulled from the trough by a pelletizer and stored as pellets.

25 The pelletized poly(lactide) was put into a drying hopper and dried at 40°C under flowing dry air. Samples were pulled after one hour and four hours. These samples were then run through a single screw Brabender® extruder, with a retention time of approximately 3 minutes. Samples 30 were analyzed for moisture by an automatic Karl Fischer apparatus and for molecular weight by GPC (the method of Example 7). The results of these tests are documented in Table 19 below.

TABLE 19

	<u>Sample</u>	<u>Extruder Temperature (C)</u>	<u>Weight Average Molecular Weight</u>
5	Initial		63,000
10	Dried 1 hour (1200 ppm H <sub>2</sub> O)	137 145 162 179	44,000 48,000 35,000 30,000
15	Dried 4 hours (150 ppm H <sub>2</sub> O)	140 140 160 178	63,000 69,000 65,000 68,000
20			

These results show the detrimental effect of water in the lactide polymer resin during melt polymerization and the need to properly dry the poly(lactide) before melt-processing.

25

Example 15Degradation of Crystalline and Amorphous Poly(lactide)

30 Two literature references disclose poly(D,L- lactide) to degrade faster than poly(L-lactide), attributing the result to crystallinity of poly(L-lactide). These are: Kulkarni et al., J. Biomed. Mater. Res., vol. 5, pp. 169-181, (1971); Makino et al., Chem. Pharm. Bull., vol. 33, 35 pp. 1195-1201, (1985). An experiment was conducted to measure the effect of crystallinity on polymer degradation and is detailed below.

An amorphous poly(lactide) sample (clear, and less than 1% crystallinity based on DSC) and a crystalline 40 poly(lactide) sample (opaque, and approximately 50% crystallinity based on DSC) were subjected to biodegradation in a compost test (50°C, with aeration). The DSC apparatus was a TA Instruments, Inc., model 910

differential scanning calorimeter with DuPont 9900 computer support system typically programmed to heating at a rate of 10°C per minute to 200°C. The samples had different optical composition, with the crystalline sample being more than 90% poly(L-lactide) and the amorphous sample being less than 80% poly(L-lactide) with the balance being either poly(D,L-lactide) or poly(meso-lactide). Samples of each polymer were subjected to a compost test (ASTM D 5338) which included mixing a stabilized compost and providing a source of humidified air while maintaining a temperature of about 50°C. The amorphous sample was completely degraded after 30 days of composting. The crystalline sample was only 23% degraded based on carbon dioxide after the same period of time.

Additional samples of these two polymers were subjected to chemical hydrolysis at 50°C (hydrolysis is believed to be the rate-limiting step in the biodegradation process). The chemical hydrolysis procedure included placing 0.1 gram poly(lactide) in 100 ml of 0.2M phosphate buffer (pH = 7.4). The samples were held for 1 week, then filtered, washed with deionized water, and dried at 25°C under vacuum. The initial weight average molecular weight for each sample was about 70,000. After 1 week the amorphous sample had a weight average molecular weight of 10,000 and the crystalline sample had a weight average molecular weight of 45,000, determined by GPC (the method of Example 7). Neither sample had significant weight loss at this time.

Both of these tests demonstrate that degradation of crystalline poly(lactide) is slower than degradation of amorphous poly(lactide).

Example 16Effect of Monomer Concentration on Film Modulus

Poly(lactide) was precipitated in methanol from a chloroform solution in order to remove the residual lactide monomer. GPC analysis (the method of Example 1) showed the precipitated polymer to contain 0.0% lactide.

The polymer was dissolved in chloroform to make a 10 wt% solution, and lactide was added back to make 5 separate solutions which, after removing the chloroform, are calculated to produce films containing 0.0, 0.2, 0.4, 1.0 and 4.0 weight% lactide in poly(lactide). These solutions were solvent cast onto glass, dried overnight at room temperature in a fume hood, and removed to a vacuum oven. The films were hung in the vacuum oven and dried at 30°C for 72 hours. GPC analysis of the vacuum-dried films showed measured lactide levels of 0.0, 0.0, 0.4, 0.7 and 3.7 wt%.

The films were then tested for film modulus using ASTM procedure D882.

The results are shown below in Table 20.

TABLE 20

	% Lactide	Tensile (psi avg.)	Std. Dev.	% Elongation	Std. Dev.	Elastic Modulus (psi avg.)	Std. Dev.
25	0	5490	636	2.85	0.14	730,000	103,000
	0	6070	123	2.85	0.22	818,000	35,000
30	0.4	5670	227	2.75	0.27	779,000	44,000
	0.7	5690	343	4.04	1.12	749,000	58,000
	3.7	5570	458	3.33	1.43	738,000	66,000

Example 17Rate of Water Uptake Versus Optical Composition

Samples of poly(lactide), made from 80% L-lactide and 20% of either D,L-lactide or meso-lactide, were ground to pass a 20 mesh screen. The samples were dried and devolatilized under vacuum then removed to a constant humidity chamber maintained at 24°C and 50% relative humidity. The rate of moisture pick-up was determined gravimetrically, with the final results verified by Karl-Fischer water analysis. The rate of moisture pickup is shown below in Table 21.

TABLE 21

Time (Minutes)	Parts Per Million Weight Gain	
	<u>L/D,L Polymer</u>	<u>L/Meso Polymer</u>
10	600	1000
30	1100	1500
60	1500	1800
120	1600	2100
870	2100	2600
Final (Karl-Fischer)	3000	2600

Example 18Standard Test of Melt Stability

A standard test for determining melt stability is as follows:

A small sample (200 grams or less) of polymer is ground or pelletized and devolatilized by holding under vacuum (about 10 mm Hg) at a temperature of 130°C or less for 18 hours. At this point the residual lactide content should be 1 wt% or less. Portions (1-5 grams) of the devolatilized sample are then placed in a 16 ml sample vial, tightly capped, and placed in a 180°C oil bath. Samples are removed at times of 15 minutes and 1 hour and analyzed for lactide content by GPC or other appropriate techniques. Lactide which may collect on the cooler



portions of the vial is included in the product work-up and test.

Melt-stabilized poly(lactide) will show less than 2% lactide in the 15 minute sample, and more preferably less than 2% lactide in the 1 hour sample. The most highly stabilized poly(lactide)s will maintain lactide contents of less than 1% in both the 15 minute and 1 hour samples, preferably less than 0.5%. An unstabilized poly(lactide) may reach the equilibrium lactide content at 180°C of 3.6 wt%, or may go even higher as lactide is driven from the polymer melt and collects on the cooler top walls of the vial.

#### Example 19

##### Water Scavenger Experiments

Dried poly(lactide) pellets were processed in a twin screw extruder to devolatilize and to prepare a portion with 0.5% by weight of a water scavenger (Stabaxol® P). The strands leaving the extruder are cooled in a water trough and chopped into pellets. Samples of the control and the test sample were then analyzed by the Karl Fischer technique for moisture content, with no drying. The control sample contained 1700 ppm water, the test sample had 450 ppm water. The control sample was then dried under nitrogen at 40°C, reducing the water content to 306 ppm. A vacuum-dried control sample had 700 ppm water.

The as-produced test sample and the dried control samples were then processed in a 1/2" single screw extruder (Brabender®) at 160°C, with a retention time of 3 minutes. The number average molecular weight for the dried control sample dropped from an initial value of 44,000 to a final value of 33,000 for the 306 ppm water sample and to 28,000 for the 700 ppm water sample. The test sample number average molecular weight dropped from an initial value of 40,000 to a final value of 33,000.

This sample shows how the water scavenger protected the polymer from moisture pick-up, imparting the same stability as a thorough drying of the control sample. Combining a water scavenger with appropriate drying is expected to give even greater stability.

#### Example 20

##### Optimization of Catalyst Concentration

A mixture of 80% L-lactide and 20% D,L-lactide was polymerized using three different levels of tin(II) bis(2-ethyl hexanoate) catalyst. Batches were prepared at initial monomer/catalyst molar ratios of 1000:1, 3000:1, and 20,000:1. Polymerization times were adjusted to reach high conversion without being excessively long and thereby causing degradation in the melt. The reaction times were 1, 2 and 20 hours, respectively. The polymerization temperature was 180°C. The polymers were ground to a coarse powder and devolatilized at 125°C and 10 mm Hg overnight. The samples were then reground and 1-gram portions of each were placed into silanized vials, 16 ml capacity. The vials were sealed and placed into an oil bath at 180°C. Vials were then removed at various times and the samples were analyzed by GPC after dissolution in chloroform. The molecular weights and lactide contents are shown below in Table 22.

TABLE 22

	Sample	Time (min)	Number Average Molecular Weight	Weight Average Molecular Weight	Lactide Weight %
5	1000:1	0	39,000	81,300	0.8
		5	28,100	57,300	2.4
		15	25,800	49,700	2.8
		30	23,100	43,800	3.7
		60	22,800	43,200	3.6
10	3000:1	0	53,100	113,600	0.6
		5	39,000	76,400	0.4
		15	30,300	65,400	1.9
		30	29,000	60,400	2.7
		60	28,200	55,200	2.8
15	20000:1	0	89,200	184,000	0.0
		5	81,200	165,100	0.0
		15	54,300	134,600	0.1
		30	51,100	119,600	0.0
		60	49,500	111,000	0.0

These results show the benefit of optimizing the catalyst level used in the polymerization process. Note that both lactide reformation and molecular weight retention benefits are realized from the reduced catalyst levels (higher monomer/catalyst ratio).

It is believed catalyst levels should be limited to 1000:1 for the high end of catalyst usage, with 3000:1 being more preferable and showing somewhat improved stability. Lower levels still, such as 20000:1, show greatly improved stability. Beyond this level it is believed the polymerization rates become too slow to be practical.

Example 21Removal of Tin Catalyst from Poly(lactide) by Precipitation

5        45 grams of L-lactide and 13 grams of D,L-lactide were  
charged with 78 milligrams of crystalline lactic acid to a  
200 ml round bottom flask. This was heated to 180°C with  
magnetic stirring in an oil bath and blanketed with dry  
nitrogen. Catalyst in the form of tin(II) bis(2-ethyl  
10 hexanoate) was added as 0.20 ml of a 0.47 g/ml solution in  
THF after the molten lactide was at temperature. The  
mixture was allowed to stir for one minute and then  
pipetted into 3 silanized glass vials, which were then  
sealed and placed into a 180°C oil bath for 75 minutes.  
15 The vials were allowed to cool and the polymer recovered by  
breaking the glass. The polymer was ground to a coarse  
powder and dissolved in chloroform to make a 10% solution.  
The polymer contained 3.8% residual monomer and had a  
number average molecular weight of 70,000 as determined by  
20 GPC measurement (the method of Example 9).

500 ml of methanol were placed in a 1-liter glass  
blender flask. The blender was turned on to medium speed  
and 50 ml of the polymer in chloroform solution was poured  
in over a period of three minutes. After one additional  
25 minute of blending the mixture was filtered, then rinsed  
with 100 ml of methanol, and dried overnight under vacuum.  
The polymer consisted of a fibrous mat. It contained 0.3%  
residual monomer and had a number average molecular weight  
of 66,900.

The measured tin level in the precipitated polymer was 337 ppm by weight, compared to a calculated value of 466 ppm for the as-produced polymer. This result indicates the feasibility of reducing residual catalyst levels in lactide polymers by solvent precipitation with the benefit of improved stability as detailed in Example 20.

10

Example 22

Samples of devolatilized poly(lactide) were tested in a Rosand Model 14°C capillary rheometer. The die was 1 mm diameter and 16 mm long, with an entry angle of 180°. The table below gives the pressure drop across the die as a function of nominal shear rate (not Rabinowitsch corrected) for various molecular weights and temperatures.

15

Table 23Results at 150°C.

	<u>Mn</u>	<u>MW</u>	<u>Temp. (°C)</u>	<u>Nominal shear rate (s<sup>-1</sup>)</u>	<u>Pressure Drop (MPa)</u>
5	34,000	70,000	150	192	2.0
				384	5.5
10				960	10.0
				1920	13.8
				4800	19.7
				9600	23.7
15	52,000	108,000	150	192	9.9
				384	15.6
				960	19.9
				1920	23.9
20				4800	29.4
				9600	----
	60,000	137,000	150	192	7.4
25				384	11.1
				960	16.6
				1920	21.0
				4800	----
				9600	----
30	183,000	475,000	150	192	19.1
				384	27.0
				960	31.4
35				1920	----
				4800	----
				9600	----

Results at 175°C.

	<u>Mn</u>	<u>MW</u>	<u>Temp. (°C)</u>	<u>Nominal shear rate (s<sup>-1</sup>)</u>	<u>Pressure Drop (MPa)</u>
5	34,000	70,000	175	192	0.4
				384	0.5
				960	3.4
10				1920	5.5
				4800	9.2
				9600	12.5
15	52,000	108,000	175	192	2.2
				384	4.6
				960	7.6
				1920	11.5
				4800	17.2
				9600	22.1
20	183,000	475,000	175	192	11.5
				384	16.6
				960	20.2
25				1920	24.4
				4800	29.9
				9600	----

30 Results at 200°C.

	<u>Mn</u>	<u>MW</u>	<u>Temp. (°C)</u>	<u>Nominal shear rate (s<sup>-1</sup>)</u>	<u>Pressure Drop (MPa)</u>
35	60,000	137,000	200	192	0.5
				384	1.6
				960	3.3
				1920	5.3
40				4800	----
				9600	13.2
45	183,000	475,000	200	192	7.0
				384	11.0
				960	14.2
				1920	17.9
				4800	21.6
				9600	----

Example 23Effect of Meso-lactide Concentration on Rate of Crystallization

- 5 Polymer samples of various optical composition were prepared by polymerizing mixtures of L-lactide and meso-lactide with Tin II bis(2-ethyl hexanoate) catalyst at a temperature of about 180°C. A portion of each sample was tested in a Mettler Differential Scanning Calorimeter Model
- 10 30 (DSC) by heating from -20°C to 200°C at 20°C/minute. The sample was then held at 200°C for 2 minutes to completely melt any crystals. The sample was thereafter rapidly quenched and reheated with the same procedure. The rapid heat-ups in this method allow a limited time for
- 15 crystallization to occur, allowing differences in crystallization rates to be observed. Results are shown in the table below.





The results show that the rate of crystallization for the polymer is decreased dramatically with the addition of small amounts of meso-lactide to the polymerization mixture.

5

#### Example 24

##### The Effect of Meso-lactide Concentration on Crystallization

Samples of devolatilized poly(lactide) of varying optical composition and with number average molecular weights in the range of 50,000 to 130,000 were prepared in a continuous pilot plant. The samples were dissolved in chloroform to a concentration of 5 grams/100cc and the optical rotation of the samples was measured to determine the concentration of meso-lactide which had been present in the monomer mixture prior to polymerization. Separate optical rotation and gas chromatography analysis of the monomer mixture confirmed that L-lactide and meso-lactide are the predominate components when meso-lactide is present at a concentration of 20% or less, and only a small correction is required for D-lactide.

Additional samples were made by polymerizing mixtures with known weights of L-lactide and meso-lactide.

All samples were subjected to an annealing procedure to develop crystallinity. The annealing procedure consisted of placing the samples in an oven at 100-105°C for 90 minutes, then lowering the temperature 10°C each 1/2 hour until the temperature reached 45°C. The oven was then shut off and the samples were allowed to cool to room temperature. The energy of the melting endotherm and the peak melting temperature were then measured using a Mettler Differential Scanning Calorimeter (DSC) apparatus with a scan speed of 20°C/minute. The energy of melting is a measure of crystallinity in the annealed samples.

Figure 3 shows the sharp decline in potential crystallinity between 9 and 12% meso content.

In contrast, a polymer sample made by polymerizing 80% L-lactide and 20% D,L-lactide showed, after annealing, a melting endotherm of 12.3 J/gm. This composition has the same enantiomeric excess in terms of lactide acid R- and S-units as does an 80% L-lactide/20% meso-lactide blend. The 20% meso-lactide containing blend showed no crystallinity after annealing, as shown by Figure 3.

10

#### Example 25

##### Effect of Plasticizer on Crystallization Rate

Devolatilized polymer samples from a continuous pilot plant were compounded with dioctyl adipate (a plasticizing agent) and/or silica with a twin screw extruder. The samples were then tested for nucleation rates using the DSC method of Example 23. The table below shows that dioctyl adipate (DOA) can increase the rate of crystallization of poly(lactide) or of a filled poly(lactide).

Table 25

	Sample	Exotherm (J/gm)	Peak Temp. (°C)	Endotherm (J/gm)	Peak Temp. (°C)
5	Base polymer	0	---	1.3	143
	Base polymer+ 8 wt% DOA	24.6	84	22.1	147
10	Base polymer+ 40 wt% silica+	2.4	86	3.9	149
15	Base polymer+ 40 wt% silica+ 5 wt% DOA	14.9	86	15.4	147
20	<u>Second upheat</u>				
	Base polymer	0	---	0	---
25	Base polymer+ 8 wt% DOA	25.0	98	24.0	143
	Base polymer+ 40 wt% silica+	0	---	0	---
30	Base polymer+ 40 wt% silica+ 5 wt% DOA	15.2	97	14.6	143

Example 26An Evaluation of Nucleating Agents

A devolatilized sample of poly(lactide) polymer was compounded with a variety of potential nucleating agents in a single screw extruder. The candidate nucleating agents were added at a nominal level of 5% by weight. The single screw extruder is not as effective of a mixer as would be used commercially, so failure to observe an effect in these tests does not mean that a candidate agent would not be effective if blended more thoroughly. A positive result in this test demonstrates potential ability to increase crystallization rates. Additives which increased crystallinity in the second upheal (on a quenched sample) were rated ++, additives which showed an effect only on the first upheal were rated +, and additives which showed no effect were rated 0.

Table 26

	<u>Additive</u>	<u>Effect</u>
	None	0
5	talc, MP1250 (Pfizer)	++
	3-nitro benzoic acid	0
	saccharin, sodium salt	++
	terephthalic acid, disodium salt	0
10	calcium silicate, -200 mesh	+
	sodium benzoate	+
	calcium titanate, -325 mesh	+
	boron nitride	+
	calcium carbonate, 0.7 micron	0
15	copper phthalocyanine	+
	saccharin	0
	low molecular weight polyethylene	0
	talc, Microtuff-F (Pfizer)	++
	talc, Ultratalc (Pfizer)	++
20	ethylene acrylic acid sodium ionomer (Allied Signal)	0
	isotactic polypropylene	+
	polyethylene terephthalate	0
	low molecular weight poly(L-lactide)	++
25	Millad 3940 (Milliken)	++
	Millad 3905 (Milliken)	+
	NC-4 (Mitsui)	+
	polybutylene terephthalate	+
	talc in polystyrene (Polycom Huntsman)	+
30	talc in polyethylene (Advanced Compounding)	++

Example 2735 Orientation and Rate of Crystallization

DSC was used to determine the effectiveness of orientation as a method of increasing the rate of crystallization. The method used is the same as in Example 23. An oriented sample will increase crystallization rate

40 primarily on the first upheal. The second upheal, which is on a sample that has been melted and quenched and therefore is no longer oriented is not expected to show crystallization. The results in the table below show an increase in crystallization rate for the nonwoven fibers of

45 Examples 3 and 4. The melting and quenching procedure (heating at 200°C for 2 minutes, followed by rapid cooling)

reduced the crystallization rate, although the effect of orientation did not disappear. It is believed that a longer hold time in the melt would eliminate the effect of orientation.

Table 27

<u>First upheat</u>				
Sample	Exotherm (J/gm)	Peak Temp. (°C)	Endotherm (J/gm)	Peak Temp. (°C)
5				
10				
Feed pellet from Example 3	0	---	0.6	147
Nonwoven, Example 3	19.4	120	19.7	150
15				
Feed pellet from Example 4	0	---	0.2	169
Nonwoven, Example 4	22.8	118	21.5	148
20				
<u>Second upheat</u>				
25				
Feed pellet from Example 3	0	---	0	---
Nonwoven, Example 3	10.5	127	9.6	148
30				
Feed pellet from Example 4	0	---	0	---
Nonwoven, Example 4	7.1	125	7.5	146



It will be understood that even though these numerous characteristics and advantages of the invention have been set forth in the foregoing description, together with details of the structure and function of the invention, the disclosure is illustrative only, and changes may be made in detail, especially in matters of shape, size and arrangement of the parts or in the sequence or the timing of the steps, within the broad principle of the present invention to the full extent indicated by the broad general meaning of the terms in which the appended claims are expressed.

WHAT IS CLAIMED IS:

1. A fabric including:
  - (a) poly(lactide) fibers formed from a melt stable lactide polymer composition comprising poly(lactide) chains having a number average molecular weight of at least 10,000; said poly(lactide) chains comprising the polymerization product of a lactide mixture containing 0.5 - 50%, by weight of lactide component, meso-lactide, the remainder of the lactide component in the lactide mixture being selected from the group consisting essentially of: L-lactide, D-lactide and mixtures thereof;
    - (i) said poly(lactide) fibers further being formed from a melt stable lactide polymer composition including no more than about 2% by weight lactide monomers.
2. A fabric according to claim 1 wherein:
  - (a) said poly(lactide) fibers comprise a nonwoven fabric.
3. A fabric according to claim 1 wherein:
  - (a) said poly(lactide) fibers further comprise fibers formed from a melt stable lactide polymer composition comprising poly(lactide) chains having a number average molecular weight from about 20,000 to about 80,000.

4. A fabric according to claim 1 wherein:  
    (a) said poly(lactide) fibers further  
comprise fibers formed from a melt stable  
lactide polymer composition comprising  
poly(lactide) chains having a number average  
molecular weight from about 50,000 to about  
250,000.
5. A fabric according to claim 1 wherein:  
    (a) said poly(lactide) fibers are  
arranged as a nonwoven fabric;  
    (b) said poly(lactide) polymer chains  
have a number average molecular weight of from  
about 10,000 to about 300,000; and,  
    (c) said fibers are formed from a melt  
stable lactide polymer composition including no  
more than about 2000 parts per million water.
6. The nonwoven fabric of claim 5 wherein  
said plurality of poly(lactide) polymer chains have  
a number average molecular weight from about 50,000  
to about 250,000.
7. The nonwoven fabric of claim 5 wherein  
said plurality of poly(lactide) polymer chains have  
a number average molecular weight from about 20,000  
to about 80,000.
8. The nonwoven fabric of claim 5 wherein  
said polymer chains are reaction products of  
polymerizing a lactide mixture comprising about 9 to  
about 50 percent by weight meso-lactide and the  
remaining lactide is substantially L-lactide and D-  
lactide.

5        9.    The nonwoven fabric of claim 5 wherein said polymer chains are reaction products of polymerizing a lactide mixture comprising about 12 to about 50 percent by weight meso-lactide and the remaining lactide is substantially L-lactide and D-lactide.

10       10.   A diaper comprising the nonwoven fabric of claim 5.

      11.   The nonwoven fabric of claim 5 further comprising an adhesive binder.

15       12.   The nonwoven fabric of claim 5, wherein said fibers are formed from a melt stable lactide polymer composition including an antioxidant selected from the group consisting essentially of: trialkyl phosphites, mixed alkyl/aryl phosphites, alkylated aryl phosphites, sterically hindered aryl phosphites, aliphatic spirocyclic phosphites, sterically hindered phenyl spirocyclics, sterically hindered bisphosphonites, hydroxyphenyl propionates, hydroxy benzyls, alkylidene bisphenols, alkyl phenols, aromatic amines, thioethers, hindered amines, hydroquinones and mixtures thereof.

30       13.   The nonwoven fabric of claim 5, wherein said fibers are formed from a melt stable lactide polymer composition including a water scavenger selected from the group consisting essentially of: carbodiimides, anhydrides, acyl chlorides, isocyanates, alkoxy silanes and mixtures thereof.

14. The nonwoven fabric of claim 5, wherein said fibers are formed from a melt stable lactide polymer composition including a desiccant selected from the group consisting of: clay, alumina, silica gel, zeolites, calcium chloride, calcium carbonates, sodium sulfate, bicarbonates and mixtures thereof.

15. The nonwoven fabric of claim 5 wherein said polymer composition further comprises:

(a) catalyst means for catalyzing the polymerization of lactide to form the poly(lactide) polymer chains, said catalyst means incorporated into the melt-stable lactide polymer composition during polymerization; and

(b) a catalyst deactivating agent in an amount sufficient to reduce catalytic depolymerization of said poly(lactide) polymer chains.

16. A compostable bag comprising the nonwoven fabric of claim 5.

17. The fabric of claim 1 wherein said poly(lactide) fibers include melt blown fibers.

18. The fabric of claim 16 wherein said melt blown fibers have a diameter of less than about 5  $\mu\text{m}$ .

19. The fabric of claim 1 wherein said poly(lactide) fibers include fibers from a spunbond process.

20. The fabric of claim 1 wherein said polymer composition further includes a plasticizer.

21. The fabric of claim 20 wherein said plasticizer is selected from the group consisting essentially of: alkyl phosphate esters, dialkylether diesters, tricarboxylic esters, epoxidized oils and esters, polymeric polyesters, polyglycol diesters, alkyl alkylether diesters, aliphatic diesters, alkylether monoesters, citrate esters, dicarboxylic esters, esters of glycerine and mixtures thereof.

10

22. The fabric of claim 1 wherein said polymer composition includes a nucleating agent comprising a crystalline polymer with a melting point greater than a processing temperature of the poly(lactide).

15

23. The fabric of claim 1 wherein said polymer composition includes a filler selected from the group consisting essentially of: cellulose, wheat, starch, modified starch, chitin, chitosan, keratin, cellulose acetate, cellulosic materials derived from agricultural products, gluten, nut shell flour, wood flour, corn cob flour, guar gum, talc, silica, mica, kaolin, titanium dioxide, wollastonite and mixtures thereof.

20

25

24. A process for the manufacture of a fabric, said process comprising the steps of:

(a) providing a melt-stable lactide polymer composition comprising:

30

- 5 (i) poly(lactide) polymer chains,  
said polymer chains being reaction  
products of polymerizing a lactide mixture  
comprising a lactide component including  
about 0.5 to about 50 percent, by weight,  
meso-lactide, with the remaining lactide  
component being selected from the group  
10 consisting of L-lactide, D-lactide and  
mixtures thereof, said polymer chains  
having a number average molecular weight  
of at least about 10,000;
- 15 (ii) lactide in a concentration of  
less than about 2 percent by weight; and  
(iii) water in a concentration of  
less than about 2000 parts per million;
- (b) extruding said polymer composition  
into fibers; and,
- 20 (c) forming the fibers into the fabric.

25 25. The process of claim 24 wherein said step  
of extruding is a melt blown process; and the  
lactide polymer composition comprises poly(lactide)  
polymer chains having a number average molecular  
weight of about 20,000 to about 80,000.

30 26. The process of claim 24 wherein said step  
of extruding is a spunbond process; and, the lactide  
polymer composition comprises poly(lactide) polymer  
chains having a number average molecular weight from  
about 75,000 to about 200,000.

27. A process according to claim 24 including a step of orienting the fibers.






FIG. 1





FIG. 2

SUBSTITUTE SHEET

FIG. 3



SUBSTITUTE SHEET

# INTERNATIONAL SEARCH REPORT

Int ional Application No  
PCT/US 93/09308

**A. CLASSIFICATION OF SUBJECT MATTER**  
IPC 5 D01F6/62 D01D5/098

According to International Patent Classification (IPC) or to both national classification and IPC

**B. FIELDS SEARCHED**

Minimum documentation searched (classification system followed by classification symbols)  
IPC 5 D01F D01D C08G

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

**C. DOCUMENTS CONSIDERED TO BE RELEVANT**

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO,A,88 10260 (BOEHRINGER INGELHEIM) 29 December 1988 see example 9 see claim 14	1
A	EP,A,0 314 245 (C.C.A. BIOCHEM B.V.) 3 May 1989 cited in the application see example 6 see claims 1,2	1
A	NL,A,299 454 (DU PONT DE NEMOURS) 25 August 1965 see example 1 see claims 1,2,4-6	1

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

\* Special categories of cited documents:

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "B" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
- "A" document member of the same patent family

Date of the actual completion of the international search

21 January 1994

Date of mailing of the international search report

10.02.94

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax (+31-70) 340-3016

Authorized officer

Siemens, T

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 93/09308

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO-A-8810260	29-12-88	DE-A-	3820299
		DE-T-	3869343
		EP-A, B	0318567
		JP-T-	2500593
		US-A-	4983745
		US-A-	5214159
EP-A-0314245	03-05-89	NL-A-	8702563
		JP-A-	1146924
		US-A-	5053485
NL-A-299454		GB-A-	1048088

**THIS PAGE BLANK (USPTO)**